

VALORIZATION OF LIGNIN IN POLYMER AND COMPOSITE SYSTEMS FOR ADVANCED ENGINEERING APPLICATIONS – A Review

Maurice N. Collins*¹, Mărioara Nechifor², Fulga Tanasă², Mădălina Zănoagă², Anne McLoughlin¹, Michał A. Stróżyk¹, Mario Culebras¹ and Carmen-Alice Teacă³

¹ *Composites Cluster, Bernal Institute, University of Limerick, Ireland,*

² *“Petru Poni” Institute of Macromolecular Chemistry, Polyaddition and Photochemistry Department,
41A Grigore Ghica-Voda Alley, 700487, Iasi, Romania*

³ *“Petru Poni” Institute of Macromolecular Chemistry,
Advanced Research Centre for Bionanoconjugates and Biopolymers,
41A Grigore Ghica-Voda Alley, 700487, Iasi, Romania*

Abstract

As fossil fuel resources dwindle and new regulations for a cleaner and safer environment come on stream, there is growing interest in developing new sustainable feedstocks for future fuels, chemicals, polymers and fibres. Therefore materials research is ever more focused on the production of green or bio-based materials and their composites. Lignocellulosic biomass has become the feedstock of choice for these new materials as cellulose and lignin are the most abundant biopolymers on the planet. Lignin is a phenolic macromolecule, the principal biological source of aromatic structures, with a complex structure which varies depending on plant species and its isolation process. Despite its high carbon content and its potential as a raw material, lignin remains underutilised. Between 40 and 50 million tons of lignin are produced worldwide per year; while some is being used for low- and medium-value applications, most is

currently treated as a non-commercialized by-product or as low value fuel to produce energy. However, with the emergence of biorefinery projects larger amounts of lignin with the potential for valorisation are being produced. Here, we summarise some of the latest developments in the field.

Keywords: lignin; blends; composites; applications

**Corresponding author:* Maurice N. Collins (e-mail address: Maurice.Collins@ul.ie)

Contents

| | |
|--|--|
| 1. Introduction | |
| 2. Lignin separation methods..... | |
| 3. Lignin fractionation..... | |
| 4. Lignin-polymer blends | |
| 5. Lignin in composite formulations | |
| 5.1 Lignin as matrix for composite materials..... | |
| 5.2 Lignin-containing composites | |
| 5.2.1 Lignin in bioplastic composites..... | |
| 5.3 Lignin in nanocomposite materials. | |
| 5.4 Lignin based carbon fibres | |
| 6. Applications of lignin-based polymer materials | |
| 6.1.Lignin as source of phenol in thermoset resins..... | |
| 6.2 Formaldehyde-free lignin-based adhesives | |
| 6.3 Lignin-epoxy resins..... | |
| 6.4 Lignin based nano carbon fibres for storage energy devices | |
| 6.5. Lignin-based hydrogels..... | |
| 6.6. Other Lignin types and applications..... | |
| 7. Concluding remarks and future developments | |

1. Introduction

Lignin is a functional polymer with relatively low molecular weight, and it represents a valuable biobased source for wide ranging applications [1-4]. It is the second most abundant polymer on the planet, is environmentally friendly, biodegradable, exhibits antioxidant properties, and displays antimicrobial activity. Interestingly, lignin is also being used as reinforcement for composite materials both in its natural fibre form and as a potential precursor for carbon fibre [5]. This review focuses on the valorisation of lignin in blends and its role as reinforcement in composites.

Lignin has been subject of previous reviews focusing on improvements of in its processability and relationships between the lignin structure and applied catalytic processes for its sustainable conversion into valuable products for applications in areas such as bioengineering [6-8], while another review focuses on value added applications involving micro- and nanostructured lignin [9].

However, this review is focused on the valorisation of lignin in advanced engineering materials. Section 1 briefly presents the main methods used for lignin separation from lignocellulosic resources. Section 2 describes the fractionation of lignin with its associated processing advantages. The third section summarises the most pertinent lignin blends with synteheic and biobased polymers. The fourth section is dedicated to the latest understanding of the role of lignin as a matrix, filler and reinforcement material in composites. Particular attention is paid to the promise of lignin as a precursor for carbon fibre and how its complex chemistry can be unravel unique biobased fibres. The fifth section details the importance of lignin in the realisation of latest strategies for the application of biobased macromolecules. Finally, we provide our outlook for the role of lignin in a post fossil based bioeconomy.

2. Lignin separation from lignocellulosic sources

Lignin extraction is technically challenging. Lignin can be isolated from various lignocellulosic sources (wood – softwood and hardwood species; crop, fiber and seed fibers plants – sugarcane, flax, jute, hemp, cotton; grasses, agricultural residues – rice and wheat straws, corn stover) but this has proven to be challenging as it is naturally resistant to chemical and enzymatic degradation. Figure 1, summarises various industrial and lab-scale separation methods. Here we summarise important sources of technical lignins which are likely to produce engineered materials, for more in-depth analysis on this topic the reader is referred to recent reviews [6-8].




Figure 1. Schematic representation of the methods used for lignin separation from different lignocellulosic sources

The pulp and paper industry represents the main source of commercial technical lignin, resulting from processes such as:

- *alkaline pulping*: otherwise known as the Kraft process involves treatment of wood fibres in a 1 M NaOH and 0.25–0.70 M Na₂S aqueous solution at 165–175°C. Depolymerisation proceeds through the cleavage of non-phenolic β-ethers and then through entrapment of quinone methide intermediates. The latter mechanism is an important improvement over the soda pulping process (NaOH only), which prevents additional condensation by formation of styryl ethers and diphenylmethane structures. However, sulphide introduces significant sulphur content into the Kraft lignin, and this impedes the subsequent valorisation of lignin. The Kraft process leads to replacement of C-O bonds of native lignins with C-C bonds inducing higher bond dissociation energies. Black liquor, contains highly complex and cross-linked lignin, is incinerated to recover Na₂S and to produce steam for power generation.

- *organosolv processes*: allows the relatively easy separation of high purity lignin at elevated temperatures using a mixture of an organic solvent (i.e., ethanol, methanol, acetone, cyclic ethers or organic acids such as acetic acid and formic acid, or combinations chosen based on their ability to dissolve lignin), and water, in the presence of acid as catalyst (added or formed in-situ from hemicellulose fraction); the most well known are: Organocell process, Alcell process, CIMV process, Chempolis process, and the AST process;

Typical organosolv treatment involves pulping of wood chips (1 part solid for 4 to 10 parts liquid) at 180–195°C in a solvent/water solution at 35–70%wt/vol at with or without acidic catalyst. The lignin, recovered by precipitation, has a high degree of purity: it is sulphur-free with low carbohydrates and ash content. Organosolv lignins are readily soluble in organic solvents

however, this leads to lignin with a high level of α -O-4 and β -O-4 cleavages while the biphenyl 5-5 content is increased, affecting the reactivities of the lignin.

One of the best known organosolv lignins is Alcell lignin (from the ethanol based process) and it is expected that once these lignins are valorised to high end applications such as for example carbon fibres, the level of investment required for the implementation of the organosolv process at scale will be justified.

- *acidic pulping*: consists of sulfite processing using excess aqueous (bi)sulfite together with either sodium-, magnesium-, calcium- or ammonium hydroxide; the lignin is dissolved in the pulping black liquor as liginosulfonate, which is separated from the other types of technical lignins, through water solubility.

- *steam explosion process*: involves pre-treatment of lignocellulosic sources with steam at about 200 °C or higher and high pressure for a short period of time followed by a rapid decompression; lignin is extracted from exploded fibrous material with either aqueous alkali or an organic solvent.

The majority of these processes induce extensive degradation of the native lignin structure. The best-known isolated lignin at lab-scale is Klason lignin, which is obtained by treating wood with sulfuric acid, the lignin is recovered as an insoluble residue after hydrolysis of polysaccharides (cellulose and hemicelluloses) to water-soluble sugars. This method for lignin isolation is usually used as an analytical means of determining lignin content, but generates a highly condensed and altered lignin, which is unsuitable for chemical characterization or further chemical investigation. The most appropriate lignin for chemical and biological studies is considered to be milled wood lignin, which is most representative of lignin in the original lignocellulose source, namely protolignin.

Some recent extraction methods involve the use of advanced solvents for selective dissolution of lignocellulosic components; these include ionic liquids (IL's) and deep eutectic solvents (DES) specifically for delignification and further valorization of isolated lignin.

3. Lignin fractionation

The variety of cross-linkages possible between the lignin chain units makes it highly heterogeneous and has been found to be challenging for its valorization [6,10]. Fractionation is a physico-chemical modification technique, which enables the separation of high molecular weight lignin chains from lower molecular weight fractions in isolated technical lignin (see Figure 2). Fractions can be separated by partial suspension in organic solvents, enzymatic treatment [11,12], selective precipitation at reduced pH and membrane assisted ultrafiltration [13,14]. Both enzymatic and ultrafiltration methods control effectively molecular weight distribution of lignin, but the techniques are costly and difficult to upscale to an industrial level [15]. All types of technical lignins have been investigated for their fractionation; however, softwood Kraft lignin is the most commonly fractionated lignin. Recent work from Dodd and Kadla has shown that two softwood kraft lignins of different origin (southern pine and Norwegian spruce) have major chemical and physical differences despite the same extraction technique [16]. However, characterization studies showed that fractions obtained from lignins of different origins follow similar trends with regards to their chemical and physical properties [17-19].

The solvent fractionation technique was first reported in 1941 by Lovell and Hibbert [20]. Methods can use one or multiple organic solvents to separate the fractions with different molecular weight, thermal properties and chemical structures [21-23]. Using a sequential approach with solvents of different polarity enables to tune the properties of the fractions obtained, by either dissolution of the insoluble fractions in successive solvents, with increasing solubility parameters [24-26], as developed by Mörck for Kraft lignin [17-19] or by

precipitation of the soluble fraction by using solvents with decreasing solubility parameters [17-19,23,27-32]. All studies show that the fractions have a lower polydispersity than the “as received lignin”. The molecular weight of the fraction modulates its thermal and structural properties: higher molecular weight fractions have a higher T_g and higher char yield, higher number of aliphatic OH and lower number of phenolic OH than the low molecular weight fractions which has lower thermal resistance [30,33]. ^{31}P NMR studies showed that the alkyl ether linkages are replaced by C-C linkages in the low molecular weight fractions while the high molecular weight ones are enriched in $\beta\text{-O-4'}$ linkages [25,29]. The modulation of the number of phenolic OH by solvent fractionation was used for improving antioxidant properties for polyurethane production [30,33] and antimicrobial activities [34,35]. Chemical protection of the hydroxyl groups in phenolic enriched softwood Kraft lignin fractions enabled Argyropoulos *et al.* [36] to synthesize lignin-poly(arylene ether sulfone) copolymers. In a similar approach, methylated lignin fractions blended with polyethylene showed improved melt spinning abilities of the softwood kraft lignin [37]. Gregorova and Sedlarik found that kraft lignin successively dissolved in dichloromethane and methanol has increased heavy metal scavenging activity [38]. A lignin-based concrete water reducer was developed based on sulfonated lignin fractionned with acetone [39]. Kraft lignin fractions have been investigated as carbon fiber precursors [10,40]. Fractionation has been used as a pretreatment to separate different molecular weight groups for lignin monomer production by catalytic depolymerisation using supercritical ethanol and ruthenium catalyst supported on activated carbon [41]. Perez used water and ethyl acetate to separate depolymerization products after supercritical water oxidation [42].




Figure 2. Separation of lignin by sequential fractionation, reproduced with permission from [25]

4. Lignin-polymer blends

Lignin has been blended with a number of polymers in order to obtain materials for high added-value applications. Efficient blending is often difficult to achieve considering the high complexity of the lignin structure and its reactivity. Lignin manifests thermoplastic behavior due to its network of strong intra- and inter-molecular hydrogen bonds [43, 44], but at high temperatures it acts as a thermoset material through occurrence of extensive cross-linking reactions [5,45]. In this context, it is of critical importance to thoroughly investigate lignin miscibility with other polymers, monitoring the evolution of phases as their compatibility or

otherwise is of real importance in gaining an understanding of the structure property relationships of lignin based blends [46].

Depending on the compatibility between lignin and different polymer matrices, the resulting blends can either form miscible blends or display a phase separation. Lignin, a relatively polar polymer due to its numerous structural OH groups, generally presents a high affinity toward polar polymer matrices. Miscible blends were observed in Kraft lignin with poly(ethylene oxide) (PEO) and poly(ethylene terephthalate) (PET) blends, while immiscible blends were found in Kraft lignin with poly(propylene) and poly(vinyl alcohol) (PVA) [47]. The compatibility in lignin blends can be evaluated by the blend morphology, investigated through visible microscopy and by assessment of lignin solubility, its concentration being determined by measuring UV absorbance of microtome section in homogeneous areas through UV microspectrophotometry methods [48].

The major drawbacks of lignin usage as an amorphous thermoplastic component in the formulation of various polymer materials is associated with its relatively high glass-transition temperature and, consequently, by its difficulty to process through thermal blending routes, when lignin undergoes self-condensation reactions through extensive cross-linking and strong intramolecular interactions under high temperature conditions, leading to inherent brittleness. Normally, these processing issues can be overcome through the blending of lignin with synthetic polymers (including co-polymerization approach) [1], biopolymers [2], through the utilization of plasticizers [3], or through chemical modification techniques [49,50].

Lignin is effective as an antioxidant and for UV protection due to its radical scavenging ability. Therefore, it is often blended with polymers such as polyethylene, PE and polypropylene, PP to improve their thermal oxidative resistance [51]. Lignin depolymerization, is often utilised to improve compatibility with the polymer matrix through decreasing its molecular weight, increasing phenolic content, and reducing aliphatic hydroxyl content [52, 53]. Lignin

depolymerization with selective bond cleavage is also performed in order to minimize lignin condensation which can often limit the conversion of lignin into value-added products [54-56].

Table 1 provides examples of lignin blends with different synthetic polymer matrices, biopolymers and other polymer systems.

Table 1. Blends of lignin with different polymer matrices

| Blend type | Polymer matrix | Example of blend | Type of lignin | Reference |
|---|---------------------------|---|--|---|
| <i>lignin-synthetic polymers blends</i> | thermoplastic polyolefins | polyethylene PE | industrial lignins (hardwood and softwood Kraft lignins, softwood organosolv lignin, wheat straw soda lignin, hydrolysis lignin from wheat) LignoBoost softwood Kraft lignin; hardwood Kraft lignin softwood Kraft lignin hardwood lignin from prehydrolysis of beech | [57] [58,59] [60] [61] |
| | | polypropylene PP | softwood Kraft lignin liquid wood (Arboform) – a mixture of lignin (30%), cellulose from hemp and flax (60%), natural additives Kraft lignin from sugarcane bagasse, hardwood Kraft lignin softwood lignosulfonates softwood kraft lignin industrial waste lignin from bagasse hardwood lignin from prehydrolysis of beech | [62] [63] [64-66] [67] [68] [69] [61] |
| | polyolefin elastomers | maleic anhydride grafted copolymers of ethylene propylene rubber EPRs | softwood lignosulfonate | [70] |
| | | ethylene propylene diene monomer rubber EPDM | pure and undegraded lignin from wheat straw (CIMV organosolv process) | [71] |
| | synthetic rubber | styrene-butadiene rubber | hardwood soda lignin (sulfur free lignin) | [72] |
| | acrylate monomers | butylmethacrylate BMA | biobutanol lignin from agricultural wastes (corn stalks and wheat straw) | [73] |

| | | | |
|----------------------------|--|---|-----------------|
| vinyl polymers | poly(vinylacetate) PVAc | acetone-soluble lignin fraction of sugarcane bagasse (organosolv lignin) | [74] |
| | poly(vinyl chloride) PVC | softwood Kraft lignin; softwood lignosulfonate; hardwood lignosulfonate hardwood organosolv lignin | [75] [76-78] |
| | poly(vinyl alcohol) PVA | hardwood Kraft lignin hardwood Kraft lignin | [79] [80] |
| polyesters | polyethylene terephthalate PET | hardwood Kraft lignin | [66] |
| | polylactic acid PLA | organosolv lignin from wheat straw | [81] |
| | | softwood organosolv lignin softwood Kraft lignin; organosolv lignin from almond shells; softwood Kraft lignin | [82] [83-85] |
| | polycaprolactone PCL | soda lignin from wheat straw | [86] |
| | | steam explosion lignin from wheat straw; softwood lignosulfonate softwood sodium lignosulfonate | [87,88] [89] |
| polyhydroxybutyrate PHB | soda lignin from sugarcane bagasse softwood sodium lignosulfonate | [90-92] [93] | |
| | polybutylene succinate | softwood lignosulfonate softwood Kraft lignin | [94] [95] |
| polyether | polyethylene oxide PEO | softwood Kraft lignin hardwood Alcell lignin | [96] [97] |
| thermoplastic elastomer | polyurethane | hardwood organosolv lignin; hardwood Kraft lignin | [98] |
| | | eucalyptus wood Kraft lignin, softwood and hardwood Kraft lignins | [99] |
| | poly(N-vinyl pyrrolidone) | organosolv lignin from annual plants | [100] |
| | | soda lignin from sugarcane bagasse | [101] |
| | polyacrylonitrile PAN | soda lignin from wheat straw | [102] |
| polyamides | polyamide 6 (nylon 6) | soda lignin from mixed wheat straw/Sarkanda grass | [103] |
| | polyamide 11 (PA11) | soda lignin from annual plants (sisal and abaca), hardwood organosolv lignin | [104] |

| | | | | |
|--|-----------------|---|---|----------------|
| | | polyaniline | hardwood Kraft lignin | [105] |
| | | polystyrene | softwood lignosulfonate softwood Kraft lignin | [106] [107] |
| | | poly (4-vinylpyridine) | alkali lignin from bamboo | [108] |
| | | poly(ester-amine) | soda lignin from mixed wheat straw/Sarkanda grass | [109] |
| | co-monomers | poly(butylene adipate-co - terephthalate) PBAT | soda lignin from mixed wheat straw/Sarkanda grass | [110] |
| | | poly(hydroxybutyrate-co- hydroxyvalerate) PHBV | softwood Kraft lignin soda lignin from steam- exploded sugarcane bagasse | [111] [112] |
| <i>lignin- biopolymer blends</i> | proteins | fish proteins | softwood Kraft lignin | [113] |
| | | wheat gluten | softwood Kraft lignin | [114] |
| | | soy protein | Kraft lignin from bamboo | [115] |
| | polysaccharides | starch | softwood Kraft lignin | [116] |
| | | | hardwood Klason lignin (acid insoluble lignin) | [117] [118] |
| | | | LignoBoost softwood Kraft lignin | [119] |
| | | | soda lignin from wheat straw and bagasse; lignosulfonates from mixed hardwoods | [120] |
| | | cellulose | softwood Kraft lignin | [121] |
| | | | ionosolv lignin from willow crop | [122] |
| | | | organosolv/Kraft lignin from eucalyptus wood | [123] |
| | chitosan | softwood Kraft lignin soda lignin from wheat straw (sulphur-free anionic sodium carbonate lignin) | [124] [125] | |
| | gelatin | soda lignin from annual plants lignosulfonate from eucalyptus wood | [126,127] [128] | |
| <i>other polymer systems</i> | | poly(butylene-adipate-co- terephthalate)-polylactide- lignin (PBAT-PLA-Lig) | softwood Kraft lignin | [129] |
| | | poly(ethylene-co-vinyl alcohol) | softwood lignosulfonate | [130] |

| | | | | |
|--|--|---|-------------------------|-------|
| | | glycol modified poly(ethylene terephthalate) PETG | softwood lignosulfonate | [131] |
| | | polycarbonate | softwood lignosulfonate | [131] |

To achieve better properties in lignin-polymer blends, chemical modification of lignin is often required [59, 60, 63, 82, 107, 115, 116]. In general, lignins, neat or chemically modified, could be used to fulfill the following functions within a blend system: reactive component in the preparation of various resins (e.g. epoxy resins, phenol formaldehyde resins (section 6.2) [132,133]) and polymers (e.g. polyurethanes (sections 4 and 5.2) [98,134-136]), nucleating agent (section 4) [86,93,94,137], surfactant [138-141], UV blocker (section 4) [51,110,142-145], thermal stabilizer (section 4) [52,53,62,146], flame retardant [147-152], adsorbing agent (section 4) [124], reinforcing filler in composites (section 5) [60,62,71,72,94,95,137,153], anti-microbial agent (biocide) [154,155], supercapacitor for energy storage (section 6.3) [156-159], carrier (for biomedical and pharmaceutical applications) (sections 4 and 5.3) [121,160], and precursor for sustainable and cost-effective carbon fibers (section 5.4) [161].

5. Lignin in composite formulations

Considerable efforts have been made in recent decades in order to valorize lignin and its derivatives into advanced composite materials driven by the accelerated fossil reserves depletion, increased environmental awareness, and the high societal demand for eco-friendly, renewable, self-sustainable materials as well as governmental incentives and legislation [162]. A wide variety of applications is already known and well documented, ranging from simple formulations up to multicomponent/multifunctional polymeric systems with tunable property capability [163]. Therefore, extensive research has been dedicated to elucidate the structure/property relationships in lignin, as well as its interactions with other materials

[164,165]. These studies have enabled the usage of lignin-based materials in advanced applications, such as bioplastics for agricultural purposes (e.g. lignin-based mulch films) and food packaging [166-168], and slow-release fertilizers and herbicides [169,170], such materials being also valuable for the production of biofuels [171-175], energy storage devices [176,177], structural modifiers [82,168,178-184], nanocomposites, nanoparticles and nanofibers [185-191].

However, the literature is inconsistent in its definition and classification of lignin-based multicomponent materials. With the terms "blends" and "composites" used interchangeably, while the role of lignin itself is often uncertain: varying between a matrix material, or an additive; either as a filler or reinforcement. In the subsequent sections we attempt to clarify these issues.

5.1 Lignin as matrix for composite materials

Since the melting temperature of lignin is in the range of 140-160°C (lower than PLA: 180-210°C) [184] and given its complex thermal behavior, it is well suited as a matrix for thermoplastic biocomposites which contain natural thermo-sensitive fillers/reinforcements, such as hemp, flax, and wood to produce fully biobased composites or green composites [192-200]. Results have shown that effective bonding between the lignin matrix and natural fibers is possible [184]. Such composites display mechanical properties which are highly dependant on fiber content, but above certain amounts of filler these properties were significantly reduced [201]. Along with weight reductions and less shrinkage, these materials proved to be effective in the attenuation of sound and noise, and oscillations [202], as well as shock absorbance [184], and are thermally stable at high temperatures not requiring flame retardants [203]. When metal nanoparticles (Pt) were deposited onto natural fibers (softwood, hemp) and subsequently incorporated into the lignin matrix, composites with reduced electrical resistance were produced [204-207]. Combining the properties of different fillers, such as natural fibers and

clays (sepiolite, organically modified Montmorillonite (MMT), it is possible to obtain lignin-based thermoplastic composites with predetermined properties in terms of mechanical and thermal performance [208].

5.2 Lignin-containing composites

Generally, it has proven difficult to incorporate high amounts of raw lignin (up to 40% w/w) into composite matrices, due to its poor compatibility, however lignin derivatives have shown promise. Thus, using Kraft lignin, it is possible to increase the content up to 80 wt%, and, consequently, significantly improve the tensile strength and Young`s moduli of matrices [163].

Composites containing different types of lignin fillers (Kraft, organosolv, soda lignin, acetylated softwood Kraft lignin - ASKL) have proven to display high performance properties [87,163]. Experimental data has confirmed that lignin addition increases the crystallization rate and degree of crystallinity, improves thermal properties (i.e., enhanced flame retardancy due to the formation of high amounts of char residue upon heating in an inert atmosphere, which reduces the combustion heat and the heat release rate), and enhances mechanical properties of matrices as shown in Table 2.

Table 2. Thermoplastic composites containing lignin as filler

| Matrix | Lignin type | Observations | Ref. |
|--------|-----------------------|---|-------|
| PP | from wood | use of 2% reactive compatibilizer with flexible segment (RCFS) | [209] |
| | | compatibilized with a hyperbranched polymer lubricant (HBPL) | [210] |
| | from wood | less loss of flexural strength and modulus and less roughness on the weathered surface | [211] |
| | | impact properties improved | [212] |
| | | modification of surface properties: polypropylene surface achieved increased hydrophilicity | [213] |
| | hardwood Kraft lignin | main objective: improving the strength properties of the composites; lignin surface modification depends on the nature of the plasma treatment: SiCl ₄ -plasma treatment resulted in silicon implantation; plasma-induced copolymerization of acryloyl chloride on lignin yielded in thin film deposition. | [214] |

| | | | |
|--|--|---|-----------|
| PE | hardwood Kraft lignin | free-radical grafting as a compatibilization method | [215] |
| | | different compatibilizing agents (PE-a-MAH and PP-a-MAH) were added to improve the interfacial interactions between matrix and filler; PE-a-MAH proved to be more effective for the PE-based composites | [216-219] |
| | | MA-g-LDPE as compatibilizer and copper(II) sulfate pentahydrate (CuSO ₄ .5H ₂ O) as dispersing agent for lignin in PE | [220] |
| | | catalytic grafting technique of lignin particles to PE | [221] |
| | | various contents of lignin (1-15%); antibacterial activity increased | [222] |
| | | addition of EVA as compatibilizer and a transition metal salt as oxo-biodegradation promoter | [223] |
| | | foams with mixed matrix LDPE-EVA and lignin particles homogeneously dispersed | [224] |
| PS - key issue: lack of compatibility between components, leading to poor properties | | content of lignin 0%-80%; addition of a compatibilizer | [107] |
| | | content of lignin 0%-80%; addition of a compatibilizer | [225] |
| | lignin from rice straw pulp | lignin complexation with cobalt (II); potential applications in the area of marked packaging materials | [226] |
| | | the matrix was grafted on the lignin nanoparticles; the formation of aggregates was observed, indicating incompatibility between the lignin particles and the PS; nanocomposites with a tailored architecture can be obtained | [227] |
| PA | Alcell (organosolv lignin from abaca and sisal) | PA11 derived from castor oil; lignin particles remained well-dispersed in the polyamide matrix | [102] |
| | organosolv lignin | PA6; lignin content prevented degradation of the composite (susceptibility of PA to UV radiation) | [228] |
| PVC | lignin treated with poly(ethyl acrylate-co-maleic anhydride) | the pretreatment of lignin resulted in improved toughness and impact strength | [229] |
| | lignin treated with poly(ethyl acrylate-co-acrylic acid) | improved thermal properties | [230] |
| | lignin with a lower molecular weight resulted by fractioning in a mixture of propanol, ethanol, and methanol | although lignin can be compatible with the PVC matrix, its rigid phenolic structure results in increased brittleness | [231] |

| | | | |
|---|--|---|-------|
| | lignin particles treated with polyacrylate | improved compatibility | [232] |
| | magnesium hydroxide-functionalized lignin | filler content 2.5-10%; notable fire resistance of composites | [233] |
| | SiO ₂ -lignin particles | filler content 2.5-10%; notable fire resistance of composites | [234] |
| PVA – main issue: to reduce miscibility | lignin nanoparticles obtained using a high-shear homogenizer | a slight increase in the thermal stability | [235] |
| | quaternized lignin | use of a formaldehyde as cross-linking agent to increase the water resistance | [236] |
| | quaternized lignin | the adsorption was strongly influenced by pH | [237] |
| ABS | | reactive compatibilization; improved flame resistance of the composite | [238] |
| TPU | ASKL | lignin content: up to 90%; the phase morphology changed from an isolated hard domain structure to an interconnected one as the physical cross-links increased | [239] |
| starch | Kraft lignin and esterified lignin | improved mechanical properties and resistance to water sorption | [116] |
| poly-siloxanes | | polydimethylsiloxane improved the water sorption resistance | [240] |
| | mixed filler: lignin as a bulky filler and silica | polysiloxane matrix was less compatible with lignin than silica, and a phase separation occurred yielding in a composite with a surface rich in hydrophobic units | [241] |
| polyaniline | | removal and recovery of Au(III) from aqueous solutions; low-cost lignin-based biosorbent | [242] |
| silica | | silica matrix; porous structures for the sorption of heavy metals | [243] |
| | | hydrated silica matrix; preliminary silica modification entailed an increased surface activity, yielding in binding a greater amount of lignin at the same weight contributions; confirmed their mesoporous structure | [244] |
| poly(<i>o</i> -phenylene diamine) | | formation of lignin-based composites on the surface of a glassy carbon electrode, due to electrochemical properties of the composite | [245] |
| PET | | lignin content up to 20%; lignin prevents the oxygen transfer toward the polymer | [246] |

The ideal multicomponent system for a thermosetting formulation requires the components to have a low viscosity prior to curing, and, therefore, it is of critical importance to find the best

suited materials (for example, unsaturated polyester resins for glass-fiber composites, epoxy resins for carbon fiber composites). Given its highly branched structure, functional groups, and free positions for substitution at the aromatic nuclei, lignin can be considered a valuable component in both thermosetting resins (as component or replacement of the hydroxylic comonomer) and thermosetting composite formulations. Even more so, as the type of lignin influences the final properties of the material; thus, different types of lignin, including Kraft lignin (KL), lignosulfonates, organosolv and enzymatic hydrolysis lignins, have been studied in these systems [247].

The main characteristic of lignin in such complex formulations is its reactivity: lignin behaves as a reactive filler. Although the vast majority of work has been on the addition of lignin to thermosetting resins, recent studies have reported lignin as filler in thermosetting composite formulations [2].

Most common thermosetting resins used for lignin-containing composites are phenol-formaldehydes (PF), polyurethanes (PU), and epoxies (EP). In PF formulations, lignin was predominately employed as resin component. However, when it is used for highly porous aerogels and cryogels containing over 80% lignin [248], it has been reported that lignin acted as both a resin component and reactive filler. Enzymatic treatment of lignin activates the phenolic rings of its structure by oxidation and this lignin modification may be employed in urea-formaldehyde-based composites [249]. It has been reported that lower amounts of resin were used as a result of lignin acting both as filler and binder. It has been shown that 3% lignin in a PU-based composite formulation, where the PU was made of hydroxyl terminated polybutadiene as soft segment in combination with toluene diisocyanate (TDI), yielded materials with poor mechanical properties because some of the lignin remained unreacted and behaved as filler, thus causing an irregular network structure [250,251]. A similar behaviour was ascertained for lignin in some rigid [252] and flexible PU foams (made of softwood Kraft

lignin, PEG with variable molecular weights and TDI) [253]. In the case of flexible foams, it was concluded that the viscoelastic properties of the foams is highly dependent on the increasing hard segment content as the lignin component is acting as a filler, and limiting crosslinking effects. A PU-based sealant containing various amounts of lignin (5-20%) has also been reported and it showed increased toughness and stiffness depending on the lignin content as it partly acted as reinforcement [254].

5.2.1 Lignin reinforced bioplastic composites

Lignin-reinforced biocomposites can be processed in extruders with modified geometry to allow good distribution of filler and prevent thermal degradation of both matrix and reinforcement components. At the same time, given that lignin is commercially available as particles or powder, other methods, such as heating-cooling mixing or extrusion-compression molding, can also be employed. Most of these biocomposites show improved thermal and mechanical properties, and can be used in odor and emission control as well. A few examples are presented in Table 3.

Table 3. Lignin as filler in biocomposites

| Biopolymer matrix | Comments | Ref. |
|--------------------------|-----------------|-------------|
|--------------------------|-----------------|-------------|

| | | |
|---|---|-------|
| polybutylene succinate (PBS) | methylene diphenyl diisocyanate (PMDI) compatibilizer; lignin weight content: 65 % | [255] |
| | lignin and switch grass as reinforcement; polymeric methylene diphenyl diisocyanate (PMDI) as compatibilizer | [256] |
| | filler: acidolysis lignin and alkali enzymatic lignin | [257] |
| | WAXD and SAXS investigations revealed that presence of the AL does not influence the crystal and supermolecular characteristics of the PHB | [258] |
| poly(3-hydroxybutyrate-co-3-hydroxyvalerate) (PHBV) | lignin was obtained from sugar cane bagasse; lignin content up to 80% | [112] |
| starch | reactive filler; lignin stabilizes the residual starch structure | [259] |
| | mixed matrix: cellulose and starch; lignin filler (1-5 wt%); hybrid green composite films with excellent mechanical properties in dry and wet states, and good thermal stability and high gas barrier | [260] |
| | matrix: glycerol-plasticized corn starch (GCS) – adipic acid modified starch microparticles (AASM) | [261] |
| PA | tall oil based polyamide | [283] |
| polybutylene adipate- ω -terephthalate | applications: non-food packaging or other short-lived applications (agriculture, sport) | [262] |
| PLA | PEG added as plasticizer | [263] |
| | three silane coupling agents: 3-aminopropyltriethoxy-silane, γ -glycidoxypropyl-trimethoxy-silane, and g-methylacryloxy-propyltrimethoxy-silane | [264] |
| | composites exhibited a six-fold increase of elongation at break and a simultaneous improvement in their tensile strength and Young's modulus | [265] |
| | comparative study using PP or PLA as matrix, and cellulose, lignin or wood flour as filler | [266] |
| natural rubber (NR) | NR/soda lignin and NR/thiolignin composites | [267] |
| | improvement of main mechanical properties | [268] |
| | comparative study on natural rubber (NR) and styrene butadiene rubber (SBR) matrices; lignin filler -forming agglomerates | [269] |
| | epoxidized natural rubber | [270] |
| | homogeneous dispersion of filler and the strong interfacial adhesion significantly enhanced the thermal stability and mechanical properties of nanocomposites | [187] |

5.3 Lignin in nanocomposite materials

In an effort to further valorise lignin, it has been successfully converted into nanoparticles, nanocapsules, nanofibers, nanotubes and other nanostructured materials [190,271-273] and

these nanomaterials are finding application in the biomedical sector (gene therapy, controlled drug release, pharmaceutical excipients [274]), food packaging, UV protection, as antioxidants, and in microfluidics [275].

Lignin nanoparticles significantly improve the thermal and mechanical properties of their corresponding polymer nanocomposites. The presence of reactive functional groups on the nanoparticle surface, enables surface modification reactions which can contribute to the interfacial adhesion between the nanofillers and matrix material. Lignin nanoparticles can be obtained by differing methods antisolvent precipitation, interfacial crosslinking, ultra-sonication, polymerization, solvent exchange, and so on, the resulting particles may have predefined shapes, size and dimensional distribution. Some recent developments in the field of nanostructured lignin-based materials are presented in Table 4.

Table 4. Lignin-based nanostructured materials

| Nanostructured material | Comments | Ref. |
|-------------------------|--|-------|
| nanoparticles | solid and hollow spherical lignin nano- and microparticles using ultrasonic spray-freezing and electrostatic stabilization; applications: cosmetics (sunscreen), pharmaceuticals (drug delivery) | [276] |
| | nanoparticles obtained by gradually addition of HCl to lignin solutions in ethylene glycol; no cytotoxicity towards yeast or microalgae | [277] |
| | addition of water (non solvent) to a solution of acetylated lignin in THF | [278] |
| | lignin alkaline solutions were added to cationic polyelectrolyte solutions of poly(diallyldimethylammonium chloride); colloidal particles (200 nm diameter) with a positive surface charge were obtained | [187] |
| | lignin nanoparticles as antioxidants and UV protection | [144] |
| | core-shell silver-lignin nanoparticles | [279] |
| | organic-inorganic hybrid materials containing lignin nanoparticles | [280] |
| | one pot synthesis of lignin nanoparticles in the presence of liquid CO ₂ as antisolvent | [281] |
| | lignin micelles for UV protection | [282] |
| | Pickering emulsions stabilized by lignin nanoparticles | [283] |
| | hyperbranched lignin copolymers able to self organize as to form nanoparticles with plasmid DNA (pDNA); promising nonviral gene vectors gene delivery applications | [284] |

| | | |
|--------------|--|-------|
| | lignin nanoparticles obtained by ultrasonication | [285] |
| | introducing water into the solution of softwood kraft lignin in tetrahydrofuran (THF) through dialysis | [286] |
| | lignin-based nanoparticles for antitumoral drug delivery | [188] |
| | organic –inorganic hybrid nanoparticles of lignin treated with iron isopropoxide | [287] |
| | lignin nano- and microparticles for stabilized emulsions | [288] |
| | polyacrylamide-g-kraft lignin nanoparticles were obtained using reversible addition–fragmentation chain transfer (RAFT) method; application: Pickering emulsions (tuning the aggregation strength while retaining interfacial activity) | [289] |
| | enzyme-assisted preparation of lignin nanoparticles (20-100 nm) with reduced polydispersity | [290] |
| | uniform size and shape nanospheres obtained by self-assembly of enzymatic hydrolysis lignin (EHL) dissolved in tetrahydrofuran by adding water under magnetic stirring | [291] |
| | lignin nanoparticles in PVA and chitosan formulations were tested for their biocide properties; applications: food packaging, drug delivery, tissues engineering, wound care | [292] |
| | lignin nanoparticles in PLA and PLA-g-GMA matrices as weathering protection and UV barrier | [293] |
| nanofibers | PLLA/PLA–lignin electrospun nanofibers with excellent antioxidant activity and good biocompatibility for biomedical applications | [294] |
| | hybrid polyester-lignin nanofibers | [295] |
| | lignin-based electrospun nanofibers with highly elastic properties | [296] |
| | electrospun defect-free nanofibers from soy protein and lignin | [297] |
| | defect-free electrospun nanocomposite fibers produced from aqueous dispersions of PVA, lignin nanoparticles and cellulose nanocrystals | [298] |
| | lignin-based electrospun nanofibers reinforced with cellulose nanocrystals | [299] |
| nanocapsules | oil-filled capsules of kraft lignin synthesized from an oil in water emulsion submitted to a high-intensity, ultrasound-assisted crosslinking of lignin at the water/oil interface; nanocapsules (diameter 300 nm) were obtained when prepared in the presence of PEGDEG | [186] |
| | hollow nanocapsules (160-390 nm) obtained by interfacial polyaddition in inverse miniemulsions; the nanocontainers can be loaded with hydrophilic substances which can be released by an enzymatic trigger | [300] |
| | nanocapsules by self-assembly of Kraft lignin | [301] |
| | pH-sensitive lignin nanocapsules for controlled delivery of hydrophobic molecules | [302] |
| nanotubes | lignin nanotubes as smart delivery vehicles for DNA; no cytotoxicity associated; no immunogenicity as in the case of viral vectors | [303] |
| | hybrid fibers made of nanocomposites containing softwood kraft lignin and MWCNTs; good porosity and surface properties | [304] |
| | MWCNTs-lignin nanocomposites with redox activity | [305] |

| | | |
|--------------------------------|---|------------|
| other nanostructured materials | ternary nanocomposite films based on PLA and hybrid nanofillers: cellulose nanocrystals and lignin nanoparticles; application in food packaging | [306, 307] |
| | PMMA nanocomposites with lignin nanoparticles obtained by free-radical graft polymerization combined with masterbatch procedure | [308] |
| | graphene exfoliation and stabilization in the presence of lignin by adsorption of lignin onto graphene surface (hybrid nanosheets) <i>via</i> π - π interactions during ultrasonic processing | [309] |

Chemical modification of lignin based nanomaterials offers the possibility to open new directions for the development of lignin-based multicomponent polymer systems with tailored properties. Even more so, given their biocompatibility, lack of cytotoxicity, and biodegradability, lignin utilisation for biomedical applications, such as drug and gene delivery, cosmetics and pharmaceuticals offers an intriguing prospect.

In blend or composite/nanocomposite formulations, raw or chemically modified, in combination with synthetic/natural polymers, assisted by specific additives (compatibilizing agents, dispersants, flame retardants, enzymes etc.), lignin proved to beneficially add to the properties' performance of the resulted polymer systems. Recent applications of lignin in thermoplastic/thermosetting and natural rubber polymer systems are presented in Tables 5-7.

Table 5. Recent applications of lignin in thermoplastic polymer systems

| Polymer matrix | Investigated properties | Lignin content | Ref. |
|----------------|--|----------------|-------|
| LDPE | mechanical and thermal properties | up to 40wt% | [60] |
| LDPE | mechanical properties and morphology | 20wt% | [310] |
| HDPE | UV weathering | 0-29wt% | [311] |
| HDPE | dimensional stability, morphology, thermal and mechanical properties | 20wt% | [312] |
| HDPE | density, morphology, mechanical and thermal properties | 40-60wt% | [313] |
| PP | mechanical and morphological properties | 50wt% | [314] |
| PP | morphology, mechanical and thermal properties | 30wt% | [315] |
| PP | mechanical, thermal and rheological properties, oxidation induction time | 10-30wt% | [316] |
| PP | physical, mechanical, and thermal properties | 50wt% | [182] |
| PP | mechanical properties, melting/crystallization behavior and morphology | 20-40wt% | [317] |
| PS | mechanical and rheological behavior | 0-80wt% | [107] |

| | | | |
|------|---|-------------|-------|
| PS | morphological structure, thermal properties, mechanical properties | 5wt% | [317] |
| PS | mechanical and thermal properties | 3.2-19.6wt% | [225] |
| PS | thermal stability, mechanical properties | 0-80wt% | [226] |
| PET | supermolecular structure and thermal properties | 0-70 wt% | [318] |
| PET | thermal stability and melting behavior, crystallinity | 0-80wt% | [246] |
| TPU | mechanical and thermal properties, rheology | up to 90wt% | [319] |
| TPU | thermo-mechanical properties, thermal stability and dielectric properties | up to 30wt% | [320] |
| TPU | mechanical and thermal properties | 5-20 wt% | [321] |
| PDMS | mechanical and thermal properties | 0-70wt% | [241] |
| ABS | thermal, mechanical, and rheological properties | 10-30wt% | [322] |

LDPE= low density polyethylene; HDPE=high density polyethylene; PP= polypropylene; PS=polystyrene; PET=poly(ethylene terephthalate); TPU= thermoplastic polyurethane; PDMS=polydimethylsiloxane; ABS=acrylonitrile butadiene styrene

Table 6. Recent applications of lignin in thermosetting polymer systems

| Polymer matrix | Investigated properties | Lignin content | Ref. |
|-------------------------|---|-----------------------|-------------|
| Epoxy resin | mechanical properties | 15-30wt% | [323] |
| Epoxy resin | mechanical and thermal properties | 2-9wt% | [324] |
| Epoxy resin | mechanical, thermal and microstructure properties | up to 60 wt% | [325] |
| Epoxy resin | thermal stability, shear strength | 5wt% | [326] |
| Epoxy resin | tensile properties | up to 50 wt% | [327] |
| PFR | wettability, contact angles | up to 40 wt% | [328] |
| PFR | thermal properties | 5-20wt% | [329] |
| Poly(vinyl ester) resin | thermo-mechanical properties | 10-30wt% | [330] |

PFR= phenol formaldehyde resin

Table 7. Recent applications of lignin in rubber polymer systems

| Polymer matrix | Investigated properties | Lignin content | Ref. |
|-----------------------|---|-----------------------|-------------|
| SBR | mechanical properties | 20-30wt% | [331] |
| NR | thermal and mechanical properties | 10-70 wt% | [3] |
| NR and SBR | morphology and mechanical properties | 50wt% | [332] |
| NR | mechanical properties | 20-30wt% | [333] |
| NR | thermal stability and mechanical properties | 15wt% | [334] |
| NR | thermal and mechanical properties | 5-40wt% | [335] |

SBR=styrene-butadiene rubber; NR= natural rubber

5.4 Lignin based carbon fibres

The first studies on carbon fibres production using lignin were carried out in the 1960s. Otanie et al. [336] produced lignin carbon fibres (LCFs) from several types of lignin (alkaline lignin, thioglignin, and lignosulfonate) using different techniques such as: dry spinning, wet spinning and melt spinning. Nippon Kayaku commercialised LCFs with the name “kayacarbon” in 1969. Several studies were carried out using these fibres for example: Tomizuka et al [337] studied the voids and structure of these LCFs. At that time, the vast majority of the studies only considered wet spinning as a production technique for LCFs thus, high molecular weight polymers such as; poly(vinyl alcohol) (PVA), or poly(acrylonitrile) (PAN) were needed to improve the processability of lignin solutions. Utilising this method tensile strength values around 0.8 GPa were reported [337,338]. During the early 1990s, several studies were focused on melt spinning for producing lignin carbon fibre precursors this offers the advantage of not requiring solvents. The main difficulties are that lignin needs to be fusible and a stabilization step is needed prior to carbonisation. During the stabilisation step the thermal behaviour of lignin changes from thermoplastic to thermoset thereby allowing the precursor fibres keep their shape during the carbonisation step. In general, for lignin stabilisation long times are required due to the slow heating rates between 0.1-2 K/min. Sudo et al. [339] reported the synthesis of phenolated lignin for carbon fibre production. The fibres were previously stabilised at 220-280 °C and they achieved tensile strength values around 0.45 GPa with a carbon yield of 40 %. Uraki et al. reported the preparation of carbon fibres from organosolv lignin [340]. They acetylated lignin in order to improve its spinnability. In addition, lignin was fractionated in low and high molecular weight fractions in order to study their behaviour during the spinning process. Precursor fibres were carbonised at 1000 °C previously stabilised at 250 °C using a heating rate of 0.5 K/min. However, the mechanical properties were very low (tensile strengths of 0.36 GPa) due to the presence of voids in the carbon fibres. At that moment, the main

problems for melt spinning lignin are associated to the thermal behaviour of lignin and its high brittleness. For these reasons, lignin polymer blends have been studied as carbon fibre precursors. The addition of a thermoplastic polymer to lignin improves two important aspects. On the one hand the precursor fibres are less brittle and on the other hand the thermoplastic behaviour of lignin is improved. In 2002 Kadla et al. reported the synthesis of carbon fibres based on lignin/poly(ethylene oxide) (PEO) blends using kraft lignin, without any chemical modification [341]. The PEO content was 5-25 % and they achieved tensile strength values of 400-550 MPa and elastic modulus 30-60 GPa. Later on, Kubo and Kadla published the effect of the synthetic polymer (PP and PET) and lignin blends on fibre properties [342]. The immiscibility between PP and lignin generates a porous structure in the final carbon fibre producing lower mechanical properties (167 MPa tensile strength and 28 GPa modulus) compared to lignin/PET blends (700 MPa tensile strength and 94 GPa modulus) that were completely miscible. Lignin copolymers with PAN were developed by Maradur et al. using radical copolymerization in DMSO [343]. Fibres were produced by wet spinning showing good morphology however, mechanical values of the carbonised samples were not provided by the authors. A thermally fusible softwood lignin, isolated by solvolysis with a mixture of polyethylene glycol 400 (PEG 400) and sulfuric acid, can be easily formed into fibres by melt-spinning at temperatures ranging from 145 to 172 °C without any modification. These lignin fibres could be converted into infusible fibres as a precursor for carbon fibres by conventional oxidative thermal stabilization processing in air or a stream of oxygen [344]. From 2012 to 2014 PEO/lignin blends were dominating the studies on carbon fibres produced by melt spinning [345] but the values of mechanical properties (400-600 MPa tensile strength and 30-40 GPa modulus) were still poor compared to PAN fibres. In 2015 composite fibres from lignin, polyacrylonitrile, and carbon nanotubes (CNT) were successfully fabricated by gel spinning and carbonised [346]. Mechanical properties were studied for those fibres and high values of

tensile strength 1.4 GPa and elastic modulus, 200 GPa were obtained. Biopolymers such as poly(lactic acid) were also used in lignin blends for carbon fibre production [347]. The immiscibility between PLA and lignin generated a heterogeneous morphology along the carbon fibres reducing the mechanical properties compared with pure lignin fibres. Values of tensile strength of around 160 MPa and 11 GPa of modulus were obtained with 20 % PLA content in the precursor fibre. In 2016, Qu et al. reported the study of carbon fibers produced from lignin-derived phenolic oil [348]. Pyrolytic lignin was isolated from pyrolysis oil of red oak. The fibres were processed into carbon fibres through melt-spinning, oxidative stabilization and carbonization at 1000 °C giving tensile strength and modulus values of around 1014 MPa and 122 GPa, respectively. More recently, other polymer blends based on lignin have been developed. Thermoplastic elastomer polyurethane was used to increase the melt spinning processability of organosolv and modified kraft lignin [98], due to the good miscibility between them (see Figure 3). Carbonized fibres showed good values of mechanical properties of tensile strength, 1 GPa and elastic modulus 80 GPa. In addition, those kinds of lignins (organosolv and modified kraft lignin) were evaluated from the point of view of thermal and dielectric behaviour determining that organosolv lignin is more suitable than kraft lignin for carbon fibre production [5]. Recently, kraft lignin was fractionated using solvents-based systems involving acetic acid + water in order to isolate the higher molecular weight fractions [349]. The results in terms of mechanical properties were promising achieving tensile strength and modulus of 1.39 GPa and 98 GPa respectively, representing the highest mechanical properties ever obtained for carbon fibers derived from low-cost, chemically unmodified lignin. Although, the mechanical properties of lignin based carbon fibres are being increased, further investigations are required in order to produce carbon fibres from lignin which can adequately replace PAN based fibres. Understanding and promoting crosslinking reactions during the stabilisation and carbonisation

step can play an important role in future investigations for high performance lignin based carbon fibres.




Figure 3. SEM images of the cross section of (a) organosolv/TPU and (b) modified-Kraft/TPU preforms fibres. Reproduced with permission from [98]

6 Applications of lignin-based polymer materials

6.1 Lignin as source of phenol in thermoset resins

Generally, adhesives for wood materials are based on the combination of formaldehyde with resorcinol or phenol, urea, on epoxy resins and on polyurethanes. Although all these polymers exhibit high tensile strength, they present drawbacks, such as the release of the carcinogen formaldehyde, flammability and the use of supplemental additives, which are usually toxic. Based on its polyphenolic structure and its similarity to phenolic resins, lignin can be added as an ingredient to phenol-formaldehyde resins, displacing phenol (and some formaldehyde) to prepare wood adhesives. Several properties of lignin, such as low glass transition temperatures

[165], low polydispersity [350], and high hydrophobicity make lignin appropriate to be used as adhesive for engineered wood like plywood panels, chip, fiber and wafer board [167]. Although lignin satisfies the requirements of a raw material for the synthesis of bio compatible adhesives, its chemical heterogeneity is a limiting factor. Moreover, lignin is processed using different chemical processes, and each process has its own advantages/disadvantages. The processing methods of the lignin have a significant influence on the adhesive properties of the synthesized phenol-formaldehyde adhesives [351].

There are two groups of lignin-based adhesives: phenol-formaldehyde adhesives when lignin is used as a partial replacement of phenol, and formaldehyde-free adhesives when lignin reacts with chemicals other than formaldehyde to generate bio-adhesives with less toxicity.

Lignin-based phenol-formaldehyde (PF) resins are synthesized by an electrophilic substitution of the phenolic groups located in ortho positions of lignin with formaldehyde. Among different types of lignin, such as liginosulfonates, Kraft lignin, organosolv lignin, enzymatic hydrolysis lignin, and soda lignin, Kraft lignin was evaluated as desirable for the substitution of phenol because of its more free-ring positions, higher molecular weight and thermal decomposition temperature by comparison with other types of lignin [352]. Table 8 presents some examples of different lignin-based phenol-formaldehyde adhesives reported in the literature, the replacement level of phenol in the synthesis of phenol-formaldehyde resin, and the properties investigated by authors.

Table 8. Lignin-based phenol-formaldehyde adhesives

| Type of lignin | Level of substitution | Investigated properties | Reference |
|---|------------------------------|--|------------------|
| methylolated lignosulfonate | 30 wt% | water absorption, thickness swelling and flexural strengths | [351] |
| organosolv lignin lignosulfonate | 50-70wt% up to 50 wt % | thermo-mechanical properties shear strength in both wet and dry conditions | [133] [353] |
| methylolated softwood ammonium lignosulfonate | 30% | chemical structure, thermal stability, and rheological behavior | [354] |
| Kraft lignin | 7 wt % and 15 wt % | water resistance | [355] |
| Kraft lignin | 50 wt % | modulus of elasticity, modulus of rupture, internal bonding strength, water absorption, and swelling thickness | [356] |
| Kraft lignin | 30 wt % | shear strength | [357] |
| Kraft lignin | 50wt% | mechanical and physical properties | [358] |
| hydroxymethylated lignin | 10–40 wt% | water resistance | [359] |
| enzymatic hydrolysis lignin | 10–60 wt %, | adhesive strength | [360] |
| methylolated organosolv lignin | up to 50 wt% | tensile strength | [361] |
| organosolv lignin | 25 to 75 wt% | thermal stability | [362] |
| lignocellulosic ethanol residue | 10–70 wt% | thermal stability | [363] |
| enzymatic hydrolysis lignin | up to 55 wt% | physical, chemical, thermal, and mechanical properties | [364] |
| hydroxymethylated lignin | 40 wt% | bonding strength | [365] |
| methylolated bio-oil-phenol formaldehyde | up to 75 wt% | physical, chemical, thermal, and mechanical properties | [366] |
| bagasse lignin | 30wt% | physical properties | [367] |
| phenolated lignin | 50 wt% | physical, chemical, thermal, and mechanical properties | [368] |
| Kraft lignin | 20 wt% | mechanical properties, stiffness, internal bond | [369] |
| enzymatic hydrolysis lignin | 10-20 wt% | bonding strengths | [370] |

6.2 Formaldehyde-free lignin-based adhesives

Lignin has lower reactivity toward formaldehyde compared to phenol and the incorporation of unmodified lignin to phenolic resin formulations is restricted to a low replacement level and shows a reduction in adhesion strength with a longer pressing time [371]. Most studies on synthesis of lignin-based adhesives without formaldehyde report the use of glyoxal [372-376] a non-volatile non-toxic dialdehyde but less reactive than formaldehyde, furfural [377] and, more recently, glutaraldehyde [378]. Calcium lignosulphonate reacted with glyoxal under alkaline condition, and the resulting lignin was mixed with polymeric diphenylmethane diisocyanate (pMDI) and applied as wood adhesives for particleboard applications [375]. The formulation containing 4,4'-diphenyl methane diisocyanate (pMDI), different ratios of methyolated lignin and glyoxal as substitute of formaldehyde in particleboard showed excellent internal bonding strengths in dry and boiled conditions in a ratio of 60/40 wt% of glyoxalated lignin/pMDI adhesive [372]. Glyoxalated lignin with a low molecular weight in the formulated pMDI shows a better internal bonding strength.

Introduction of triacetin into the lignin-based adhesives enhanced the curing process of the methyolated lignin with pMDI and improved the modulus of elasticity value [378]. Glyoxalated lignin mixed equally with tannin, followed by crosslinking with hexamine (5 wt % of tannin) was reported as a bio-based adhesive without incorporating any synthetic resin [373,379]. Another formaldehyde-free resins showed good thermal stability and char yield [380]. A formaldehyde-free wood adhesive using Kraft lignin and polyethylenimine (PEI) was designed for the manufacture of plywood. The sample containing lignin/PEI in weight ratio of 2:1 showed the highest shear strengths (dry shear strength, water-soaking- and drying strength, boiling water test/dry strength, and boiling water test/wet strength) and the greatest water resistance [381,382]. The physico-mechanical properties of a modified ammonium lignosulfonate (AL)/PEI mixture as a green binder in preparation of medium density fiberboard

(MDF) were evaluated [383]. The optimum performance was obtained at 20 wt % binder with AL /PEI weight ratio of 7:1 after curing at 170 °C for 7 min. The relative crystallinity of the composites was significantly improved. A combination of polyfurfuryl alcohol (PFA) and lignin, where furfural and lignin replaced formaldehyde and phenol in polyphenol (PF) resins, respectively, were prepared in lignin contents of 20 and 30 wt % [384].

The presence of lignin led to the formation of a slightly stiffer matrix with better impact strengths. Similar lignin-furfural based adhesives show a better performance because the lower molecular weight of lignin has better mobility and exhibited better mechanical properties. The influence of furfural content, pH, curing temperature and pressure on the mechanical properties were studied [377]. Enzymatic hydrolysis lignin (EHL) performed in oxygen plasma improved the physical and mechanical properties of EHL. The modulus of elasticity, modulus of rupture, and internal bonding strength increased while thickness swelling decreased with increasing the time and power of the plasma processing [385]. In a recent study phenol portion from phenol formaldehyde resin was replaced by an agricultural-based lignin, which was produced as a byproduct of a cellulosic bioethanol process through dilute-acid pretreatment and enzymatic hydrolysis from corn stover. The PF resin was formulated using isolated lignin under alkaline condition [386].

6.3 Lignin-epoxy resins

Noteworthy, there have been several reports in the literature that presents the interest in preparing lignin-epoxy resins. For these applications the waste lignin derived from the common pulp and paper processes (Kraft, soda, etc.) must be purified (precipitation, deionisation, etc.) or one can use lignin from the less condensing pulping processes such as Alcell, non-wood fibres pulping. Phenolated Kraft lignins with different purity degrees were prepared and tested as adhesives for plywood. When the phenolation of Kraft lignin was acid catalyzed the strength and water resistance of the final resin were higher. The experimental tests evidenced that lignin

purity did not influence the adhesive properties of the resulting resins [387-389]. Some scientific papers show that significant lignin loads (<50 wt%) could be incorporated into the epoxy resin and they exhibited good electrical (dielectric constant, loss in dielectric tangent angle and dielectric rigidity, volume and surface resistivity,) and mechanical properties, as well as high impact toughness (Charpy impact strength) as compared with the lignin free phenol epoxy resins [390-392]. Later on, lignin was incorporated into the resin for fabrication of printed circuit boards [393]. Some other reports show that epoxy modified lignin-based resins can be prepared in significant quantities by purification techniques involving reaction of lignin with epichlorohydrin and subsequent recycling of excess of epichlorohydrin and filtration to purify the resulting resin [388,394].

6.4 Lignin based nano carbon fibres for energy storage devices

Currently, there are several kinds of devices able to store energy such as: fuel cells, batteries, combustion engines, supercapacitors and capacitors [395,396]. Basically, there are two parameters characteristic for all devices employed in energy storage, one is the energy density and the other one is the power density. The energy density gives information about the amount of energy that the device can accumulate per unit mass, the power density is related with the power output that the device is able to supply per unit mass. Batteries show high energy density however low power density; in contrast capacitors exhibit a high power density and low energy density. Consequently, batteries store energy well, however the energy output is low. On the other hand capacitors are able to fast supply energy, however, they cannot store energy well. In the region with intermediate properties are the supercapacitors. During the last decade, carbon nanofibers (CNFs) produced by electrospinning have been studied as electrodes for both kind of devices, supercapacitors and batteries. Although, the vast majority of studies published until

now, use PAN as precursor material [397], below we describe the few papers that use lignin based precursors.

Lai et al published the synthesis of electrospun CNFs made from lignin/PVA solutions [398]. The gravimetric capacitance of CNFs produced from lignin/PVA(70/30) exhibited 64 F.g^{-1} at 400 mA.g^{-1} and 50 F.g^{-1} at 2000 mA.g^{-1} . The CNFs electrodes also exhibited excellent cycling durability/stability, and the gravimetric capacitance only was reduced by around 10% after 6000 cycles of charge/discharge. In 2015, You et al. [399] reported the preparation of Lignin-based activated carbon fibers by electrospinning of hardwood acetic acid lignin. These CNTs showed good capacitance, 133.3 F g^{-1} at a current charge of 1 A g^{-1} . High energy and power density for this device (42 Wh kg^{-1} and 91 kW kg^{-1} , respectively) were also achieved. Electrodes produced from soda lignin and PEO CNFs show good potential for supercapacitors as was reported by You et al. [400]. Lignin/PEO CNFs electrodes with an organic electrolyte exhibited an impedance of 1.6Ω and a specific capacitance of 92.6 F g^{-1} at a scan rate of 1 A g^{-1} . In addition, hybrids materials based on PAN/lignin/ NiCo_2O_4 were studied by Lei et al in 2017 [401]. They produced PAN/lignin based carbon nanofibers with different contents of lignin. Afterwards, the NiCo_2O_4 oxides were deposited on the surface of CNFs by hydrothermal reaction. They developed flexible PAN/lignin/ NiCo_2O_4 CNFs electrodes giving a high specific capacitance of 1757 F g^{-1} at 2 mA cm^{-2} and excellent cycle resistance with 138% of capacitance retention after 5000 cycles at 7 mA cm^{-2} .

There are only a few examples of electrodes made from lignin based solutions in the last decade. Nitrogen-doped free standing fused carbon fibrous mat, fabricated from organosolv lignin/ PEO (90:10) blend via electrospinning followed by carbonization and thermal annealing in the presence of urea, was prepared by Wang et al. [402]. The fused carbon fibres without nitrogen doping exhibited high specific capacity up to 445 mA h g^{-1} at a current density of 30 mA g^{-1} (comparable to PAN derived carbon nanofibers) and good cyclic stability at different current

rates. After thermal annealing in the presence of urea, the charge capacity was further improved to as high as 576 mA h g^{-1} and still maintained a good capacity of about 200 mAh g^{-1} even at a high current rate of 2000 mA g^{-1} . In 2014 Jin et al. reported CNFs electrodes for sodium ion batteries made from PAN/lignin solutions [403]. With a mass ratio PAN/lignin of 5/5 which exhibit a high reversible capacity of $292.6 \text{ mA h g}^{-1}$ with an initial efficiency of 70.5% at a constant current density of 0.02 A g^{-1} . Research on lignin based batteries is currently at an early stage. There are difficulties associated with electrode preparation as some lignins are impossible to stabilise and therefore convert to carbon nanofibres and due to the occurrence of irregular morphologies as a result of electrospinning low viscosity lignin solutions.

6.5 Lignin-based hydrogels

Hydrogels are defined as physically or chemically cross-linked three-dimensional hydrophilic networks that swell in water or aqueous solutions. Hydrogels present interesting properties such as highly water absorption and retention, good biocompatibility, tissue-mimicking ability, and controlled diffusion [404], making them suitable for a large number of applications such as tissue engineering, absorption, drug delivery and biosensors [405]. Hydrogels can be synthesized using several methods including free radical polymerization, irradiation, as well as chemical and physical cross-linking of polymers. Lignin has become the focus of many studies in the field of hydrogel development due to its inherent properties such as biocompatibility, biodegradability, low toxicity, and importantly its susceptibility to enzymatic degradation [405]. Early works have shown that the preparation of lignin hydrogels by graft copolymerization between acrylamide (AM) and poly(vinyl alcohol) (PVA) with alkaline or kraft lignin (AM-PVA-g-lignin) and then by mixing with acrylamide monomer was possible [406]. Compared with Kraft lignin hydrogel, the alkaline lignin hydrogel showed very high swelling ratios and slower water uptake and deswelling rates which can be attributed to its

network structure [406]. Xanthan-lignin networks were reported by Raschip et al. [407] as being obtained by crosslinking xanthan and lignin in the presence of epichlorohydrin. This study showed that the structure of lignin strongly influenced the swelling process. Poly(ethylene) glycol diglycidyl ether (PEGDGE) has also been utilised as a crosslinker for several technical lignins (see Figure 4) producing highly swollen gels, which exhibited mechanical stability [408]. The authors suggested that that these gels could potentially be used for minimizing drought stress and enhancing irrigation efficiency, especially in sandy soils with low water retention in arid regions. Polyurethane/lignin hydrogels have been obtained by reacting acetic acid with lignin and isocyanate group-terminated polyurethane ionomers [409]. Those hydrogels possessed pH-sensitivity and showed potential as coating materials for slow-release fertilizers [409].




Figure 4. Reaction scheme of PEGDGE-mediated cross-linking of lignin substructures under alkaline conditions. Reproduced with permission from [408]

Bentonite/sodium lignosulfonate graft-polymerized with acrylamide and maleic anhydride (BLPAMA) have produced hydrogels for lead removal reaching a Pb^{2+} adsorption capacity of 1.045 mmol/g at pH=5.0 [410]. Similar investigations were carried out by Xiaodong Zhang, et al. using lignin/clay hydrogels for dye (methylene blue) removal [411]. These hydrogels were prepared by grafting acrylamide and *N*-isopropyl acrylamide onto lignin, along with the incorporation of montmorillonite assisted by ultrasonication (lignin-g-p(AM-co-NIPAM)/MMT) as it was shown in Figure 5. The adsorption data fitted well the Langmuir and Freundlich models, with an optimum adsorption value of 9646.92 mg/g. Other hydrogels were prepared starting from lignin and poly(ethylene glycol) methyl ether methacrylate (PEGMA)/cyclodextrin (α -CD) by atom transfer radical polymerization [412]. These hydrogels showed mechanically responsiveness, good rheological properties and excellent self-healing ability. Given their lignin biodegradable core, the hyperbranched supramolecular hydrogels are expected to be potentially biodegradable. Drug delivery is one of the applications for lignin based hydrogels as reported by Xiaohong Wang, et al [413]. Sodium lignosulphonate-grafted poly(acrylic acid-co-poly(vinyl pyrrolidone)) hydrogel (SLS-g-P(AA-co-PVP) was prepared by ultrasound-assisted synthesis. Amoxicillin was used as model drug to study the release properties. It was found that the release behaviour can be controlled by adjusting the pH value of the medium. In simulated gastric fluids (SGF) (pH around 1.2), the cumulative release rate was up to 51.5% in 24 h and about 32% for 2 h. But for the simulated intestinal fluids (SIF) (pH around 7.4), the cumulative release rate reached 84.5% in 24 h and 63.3% after digestion and absorption for 5 h [413].




Figure 5. Schematic process of the preparation and adoption process of lignin-g-p(AM-co-NIPAM)/MMT. Reproduced with permission from [411]

Hydrogels based on soluble glycinated Kraft lignin (WS/KL) and hyaluronan (NaHy) were prepared [414]. The lignin was modified by a Mannich reaction in order to improve the water solubility of lignin. It was found that the creep resistance and creep recovery of NaHy hydrogels were improved by the incorporation of WS/KL up to 3% (w/w). However, the swelling capacity of hydrogels was low, but the cytotoxicity tests demonstrated that the final hyaluronan/lignin hydrogels were non-toxic materials.

The combination of cellulose and lignin has been also studied in order to develop hydrogels [415,416]. Reinforced PVA hydrogels containing lignin and cellulose nanofibrils were obtained and it was shown that the mechanical and rheological properties of the reinforced PVA

hydrogels can be tuned by varying lignin and cellulose content [415]. In addition, lignin and cellulose can be combined in supercapacitors as it was reported by Wenbin Zhong, et al. [416]. They produced electrodes using SWCNTs dispersed in lignosulfonate solutions submitted to an autoclave hydrothermal treatment at 180°C for 12 h. Cellulose hydrogels were used as electrolyte mixed with NaOH solutions. The supercapacitors showed excellent electrochemical stability (1000 bending cycles) and specific capacitance values of 292 F/g.

There is little doubt about the potential valorisation of lignin through its use in hydrogel formulations due to the large number of applications in energy storage, biomedical and pharmaceuticals, adsorbents and electrochemical sensors. Looking to the future it is likely that the deployment of lignin based hydrogels will be in conjunction with newly developed processing techniques such as advanced printing technologies.

6.6 Other Lignin types and applications

Lignin has been identified as a potential renewable source of biodegradable and safer antioxidants and stabilisers. Substantial work has been reported to date on the identification of material characteristics that are critical to tailor the antioxidant and stabilising effects of differing lignins [35,51,146]. It is clear that the performance of lignin strongly depends on its origin, extraction method and subsequent modification as described previously [417]. It is generally agreed that lignin acts as an antioxidant through scavenging of free radicals. For example, the importance of non-etherified phenolic hydroxyl groups (acting as scavengers of peroxy radicals) has been demonstrated [58,418]. While it has been demonstrated that structural variations such as higher molecular weights and polydispersity were detrimental on antioxidant activity [418,419]. Radical scavenging ability also plays an important role on thermal stabilisation of lignin, therefore increased phenolic contents offer superior thermal

stability in blends with other polymers [52] highlighting that thermo-oxidative stabilisation activity is strongly related to antioxidant activity for lignins.

Poly-(caffeyl alcohol) (PCFA) homopolymer called C-lignin was recently discovered in the seed coats of Vanilla orchid (*Vanilla planifolia*) [420] and various cacti species [421]. Structural analysis reveals that the polymer is a benzodioxane chain derived entirely from caffeyl alcohol monomers (G units lacking the methyl group on the 3-oxygen) linked head to tail via radical coupling reaction. It is postulated that the homogeneity of the polymer could potentially improve biomass utilisation as depolymerisation of lignin to a single product can be controlled, as schematically shown in figure 6 [422-424]. C-lignin extracted from Vanilla seeds has been successfully electrospun into fibres without any chemical pretreatment or addition of other polymers [425]. Following carbonisation at 900°C, carbon fibres from C-lignin had a diameter of about 10µm, comparable axial moduli and superior transverse moduli compared to Kraft and commercial CF. However despite this potential in engineering applications, its commercial value remains unclear as it is not available in bulk quantities from traditional biomass sources. Another new type of lignin, called 5H lignin, has been identified via NMR analysis of *Escobaria dasyacantha* seeds [421]. This type of lignin is derived from polymerisation of 5-hydroxyconiferyl alcohol (S unit lacking methyl group at position 5 of the aromatic ring).

Thermoelectricity could be another potential application for lignin allowing the production of energy from temperature gradients. Thermoelectric effects have been observed in carbon nanofibres derived from lignin, with authors able to obtain p-type to n-type semiconducting behaviour with a thermoelectric power factor of 9.27 µW cm⁻¹ K⁻² [426]

In summary, Lignin structures and yields in transgenic plants have been the focus of extensive research [6]. While these attempts to control the structure or yield of lignin have also provided important information about its biosynthetic pathways.




Figure 6. Schematic representation of C-lignin and its potential for controlled depolymerisation.

7 Concluding remarks and future developments

Lignin is the most important aromatic polymer derived from renewable resources, it displays both a unique and complex chemical structure, is abundant in nature and does not compete with the food production chain. Lignin remains a subject of strong interest in industry and academia, as vouched by the impressive amount of data accumulated lately in the literature. Despite the knowledge and technical progress in terms of its valorization, much as yet to be achieved. Progress has been made on its role as a resource for the production of renewable fuels and chemicals mainly associated with recent advances reported in bioengineering, biorefining and catalysis. However, research on lignin as a precursor for carbon fibre at both micron and nanoscale is in its infancy. The future potential of lignin in medicine and healthcare, pharmaceuticals and cosmetics, food packaging and energy is yet to be established and is sure to be the subject of investigations in the coming years.

Future research directions are likely to be aimed at developing nanostructured materials for advanced applications (energy storage, thermoelectric devices, bio-sensors, controlled drug delivery, gene therapy, theranostic systems). Investigations are required to establish the complex interactions of these newly designed materials with living tissues, to determine targeting cues and to provide solution based on controlled release mechanisms,

chemical/enzymatic degradation activity under physiological conditions need to be tailored, while elimination procedures to avoid tissue accumulation and side effects must be realised.. Once these principles are established it is likely that lignin will play a role in the development of 3D printing and bioprinting technologies [395 427].

Ultimately, the valorization of lignin will be strongly influenced by its chemical and functional versatility, which will demand specific approaches in terms of processing and chemical modification. The next steps in this direction will involve the understanding of structure/property/function relationships in these materials while offering the possibility of tuning the macroscopic properties of the materials through the control of the structure, morphology and chemistry at nano scale.

References

- [1] C. Wang, S. S. Kelley, R. A. Venditti, Lignin-based thermoplastic materials, *ChemSusChem* 9 (2016) 770-783.
- [2] V. K. Thakur, M. K. Thakur, P. Raghavan, M. R. Kessler, Progress in green polymer composites from lignin for multifunctional applications: A review, *ACS Sustain. Chem. Eng.* 2 (2014) 1072-1092.
- [3] A. Duval, M. Lawoko, A review on lignin-based polymeric, micro- and nano-structured materials, *React. Funct. Polym.* 85 (2014) 78-96.
- [4] W.O.S. Doherty, P. Mousavioun, C.M. Fellows, Value-adding to cellulosic ethanol: Lignin polymers, *Ind. Crops Prod.* 33 (2011) 259-276.
- [5] M. Culebras, M.J. Sanchis, A. Beaucamp, M. Carsí, B.K. Kandola, A.R. Horrocks, G. Panzetti, C. Birkinshaw, M.N. Collins, Understanding the thermal and dielectric response of organosolv and modified kraft lignin as a carbon fibre precursor, *Green Chem.* 20 (2018) 4461–4472.
- [6] R. Rinaldi, R. Jastrzebski, M. T. Clough, J. Ralph, M. Kennema, P. C. A. Bruijninx, B. M. Weckhuysen, Paving the way for lignin valorisation: Recent advances in bioengineering, biorefining and catalysis, *Angew. Chem. Int. Ed.* 55 (2016) 8164-8215.
- [7] A. J. Ragauskas, G. T. Beckham, M. J. Bidy, R. Chandra, F. Chen, M. F. Davis, B. H. Davison, R. A. Dixon, P. Gilna, M. Keller, P. Langan, A. K. Naskar, J. N. Saddler, T. J. Tschaplinski, G. A. Tuskan, C. E. Wyman, Lignin valorization: Improving lignin processing in the biorefinery, *Science* 344 (2014) 1246843.
- [8] S. Constant, H. L. J. Wienk, A. E. Frissen, P. de Peinder, R. Boelens, D. S. van Es, R. J. H. Grisel, B. M. Weckhuysen, W. J. J. Huijgen, R. J. A. Gosselink, P. C. A. Bruijninx, New insights into the structure and composition of technical lignins: a comparative characterisation study, *Green Chem.* 18 (2016) 2651-2665.

- [9] S. Beisl, A. Friedl, A. Miltner, Lignin from micro- to nanosize: Applications, *Int. J. Mol. Sci.* 18 (2017) 2367 (24 pages).
- [10] W. Boerjan, J. Ralph, M. Baucher, Lignin biosynthesis, *Ann. Rev. Plant Biol.* 54 (2003) 519-546.
- [11] Q. Li, S. Xie, W.K.Serem, M.T.Naik, L. Liu, J.S.Yuan, Quality carbon fibers from fractionated lignin, *Green Chem.* 19 (2017) 1628-1634.
- [12] S. Xie, Q. Li, P. Karki, F. Zhou, J.S.Yuan, Lignin as renewable and superior asphalt binder modifier, *ACS Sustain. Chem. Eng.* 5 (2017) 2817-2823.
- [13] I. Brodin, E. Sjöholm, G. Gellerstedt, Kraft lignin as feedstock for chemical products: The effects of membrane filtration, *Holzforschung* 63(2009) 290-297.
- [14] O. Sevastyanova, M. Helander, S. Chowdhury, H. Lange, H. Wedin, L. Zhang, M. Ek, J.F. Kadla, C. Crestini, M.E. Lindström, Tailoring the molecular and thermo-mechanical properties of kraft lignin by ultrafiltration, *J. Appl. Polym. Sci.* 131 (2014) 40799.
- [15] Q. Li, M.T. Naik, H.S. Lin, C. Hu, W.K. Serem, L. Liu, P. Karki, F. Zhou, J.S.Yuan, Tuning hydroxyl groups for quality carbon fiber of lignin, *Carbon* 139 (2018) 500-511.
- [16] A. P. Dodd, J. F. Kadla, S. K. Straus, Characterization of fractions obtained from two industrial softwood Kraft lignins. *ACS Sustain. Chem. Eng.* 3(1) (2015) 103-110.
- [17] R. Mörck, H. Yoshida., K. P. Kringstad, Fractionation of Kraft lignin by successive extraction with organic solvents I. Functional groups, ¹³C NMR spectra and molecular-weight distributions, *Holzforschung* 40 (1986) 51-60.
- [18] R. Mörck, A. Reimann, K. P. Kringstad, Fractionation of Kraft lignin by successive extraction with organic solvents. III. Fractionation of Kraft lignin from birch, *Holzforschung* 42 (1988) 111-116.
- [19] H. Yoshida, R. Mörck, K. P. Kringstad, H. Hatakeyama, Fractionation of Kraft lignin by successive extraction with organic solvents II. Thermal properties of Kraft lignin fractions, *Holzforschung* 41 (1987) 171-176.
- [20] E.L. Lovell, H. Hibbert, Studies on lignin and related compounds. LII. New method for the fractionation of lignin and other polymers, *J. Am. Chem. Soc.* 63 (1941) 2070-2073.
- [21] V. Passoni, C. Scarica, M. Levi, S. Turri, G. Griffini, Fractionation of industrial softwood Kraft lignin: solvent selection as a tool for tailored material properties, *ACS Sustain. Chem. Eng.* 4 (2016) 2232-2242.
- [22] T. Saito, J.H. Perkins, F. Vautard, H.M. Meyer, J.M.Messman, B. Tolnai, A. K. Naskar, Methanol fractionation of softwood kraft lignin: Impact on the lignin properties, *ChemSusChem.* 7 (2014) 221-228.
- [23] C.G. Boeriu, F.I. Fițigău, R.J.Gosselink, A.E. Frissen, J. Stoutjesdijk, F. Peter, Fractionation of five technical lignins by selective extraction in green solvents and characterisation of isolated fractions, *Ind. Crops Prod.* 62 (2014) 481-490.
- [24] A. Duval, F. Vilaplana, C. Crestini, M. Lawoko, Solvent screening for the fractionation of industrial kraft lignin, *Holzforschung* 70 (2016) 11-20.
- [25] S. Y. Park, J. Y. Kim, H. J. Youn, J. W. Choi, Fractionation of lignin macromolecules by sequential organic solvents systems and their characterization for further valuable applications, *Int. J. Biol. Macromol.* 106 (2018) 793-802.
- [26] N. Kumar, S. Vijayshankar, P. Pasupathi, S. N. Kumar, P. Elangovan, M. Rajesh, K. Tamilarasan, Optimal extraction, sequential fractionation and structural characterization of soda lignin, *Res. Chem. Intermediat.* 44 (2018) 5403-5417.
- [27] X. Jiang, D. Savithri, X. Du, S. Pawar, H. Jameel, H.M. Chang, X. Zhou, Fractionation and characterization of kraft lignin by sequential precipitation with various organic solvents, *ACS Sustain. Chem. Eng.* 5 (2016) 835-842.

- [28] C.Z. Cui, R.K. Sun, D.S. Argyropoulos, Fractional precipitation of softwood Kraft lignin: Isolation of narrow fractions common to a variety of lignins, *ACS Sustain. Chem. Eng.* 2 (2014) 959-968.
- [29] Y.Y. Wang, M. Li, C.E. Wyman, C.M. Cai, A.J. Ragauskas, Fast fractionation of technical lignins by organic cosolvents, *ACS Sustain. Chem. Eng.* 6 (2018) 6064-6072.
- [30] H. Sadeghifar, T. Wells, R. Khuu Le, F. Sadeghifar, J.S. Yuan, A.J. Ragauskas, Fractionation of organosolv lignin using acetone:water and properties of the obtained fractions. *ACS Sustain. Chem. Eng.* 5 (2017) 580-587.
- [31] A.-S. Jääskeläinen, T. Liitiä, A. Mikkelsen, T. Tamminen, Aqueous organic solvent fractionation as means to improve lignin homogeneity and purity, *Ind. Crops Prod.* 103 (2017) 51-58.
- [32] J. Domínguez-Robles, T. Tamminen, T. Liitiä, M. S. Peresin, A. Rodríguez, A.-S. Jääskeläinen, acetone fractionation of kraft, organosolv and soda lignins, *Int. J. Biol. Macromol.* 106 (2018) 979-987.
- [33] A. Arshanitsa, J. Ponomarenko, T. Dizhbite, A. Andersone, R. J. A. Gosselink, J. der Putten, M. Lauberts, G. Telysheva, Fractionation of technical lignins as a tool for improvement of their antioxidant properties, *J. Anal. Appl. Pyrol.* 103 (2013) 78-85.
- [34] G. Wang, Y. Xia, B. Liang, W. Sui, C. Si, Successive ethanol-water fractionation of enzymatic hydrolysis lignin to concentrate its antimicrobial activity, *J. Chem. Technol. Biotechnol.* 93 (2018) 2977-2987.
- [35] J. L. Espinoza-Acosta, P. I. Torres-Chávez, B. Ramírez-Wong, C. M. López-Saiz, B. Montaña-Leyva, Antioxidant, antimicrobial, and antimutagenic properties of technical lignins and their applications, *BioResources* 11 (2016) 5452-5481.
- [36] D. S. Argyropoulos, H. Sadeghifar, C. Cui, S. Sen, Synthesis and characterization of poly(arylene ether sulfone) kraft lignin heat stable copolymers, *ACS Sustain. Chem. Eng.* 2 (2014) 264-271.
- [37] H. Sadeghifar, D.S. Argyropoulos, Macroscopic behavior of kraft lignin fractions: melt stability considerations for lignin–polyethylene blends, *ACS Sustain. Chem. Eng.* 4 (2016) 5160-5166.
- [38] A. Gregorova, V. Sedlarik, Characterization of structural and physical properties of dichloromethane- and methanol-fractionated Kraft lignin and its adsorption capacity of Cu (II) and Ni (II) ions, *Desalin. Water Treat.* 57(23) (2016) 10655-10663.
- [39] S.Y. Li, Z. Li, Y. Zhang, C. Liu, G. Yu, B. Li, X. Mu, H. Peng, Preparation of concrete water reducer via fractionation and modification of lignin extracted from pine wood by formic acid, *ACS Sustain. Chem. Eng.* 5(5) (2017) 4214-4222.
- [40] Q. Li, W. K. Serem, W. Dai, Y. Yue, M. T. Naik, S. Xie, P. Karki, L. Liu, H.-J. Sue, H. Liang, F. Zhou, J. S. Yuan, Molecular weight and uniformity define the mechanical performance of lignin-based carbon fiber, *J. Mater. Chem. A*, 5 (2017) 12740-12746.
- [41] J.-Y. Kim, S. Y. Park, J. H. Lee, I.-G. Choi, J. W. Choi, Sequential solvent fractionation of lignin for selective production of monoaromatics by Ru catalyzed ethanolysis. *RSC Adv.* 7(84) (2017) 53117-53125.
- [42] E. Perez, C. O. Tuck, M. Poliakoff, Valorisation of lignin by depolymerisation and fractionation using supercritical fluids and conventional solvents, *J. Supercrit. Fluids* 133 (2018) 690-695.
- [43] A. Sakakibara, A structural model of softwood lignin, *Wood Sci. Technol.* 14 (1980) 89-100.
- [44] H. Nimz, Beech lignin—Proposal of a constitutional scheme, *Angew. Chem. Int. Ed.* 13 (1974) 313-321.

- [45] S. Kubo, J. F. Kadla, Hydrogen bonding in lignin: A Fourier transform infrared model compound study, *Biomacromolecules* 6 (2005a) 2815–2821.
- [46] S. Sen, S. Patil, D. S. Argyropoulos, Thermal properties of lignin in copolymers, blends, and composites: A review, *Green Chem.* 17 (2015) 4862–4887.
- [47] J. F. Kadla, S. Kubo, Lignin-based polymer blends: analysis of intermolecular interactions in lignin–synthetic polymer blends, *Compos. Part A* 35 (2004) 395–400.
- [48] C. Pouteau, S. Baumberger, B. Cathala, P. Dole, Lignin–polymer blends: evaluation of compatibility by image analysis, *C. R. Biol.* 327 (2004) 935–943.
- [49] S. Laurichesse, L. Averous, Chemical modification of lignins: Towards biobased polymers, *Prog. Polym. Sci.* 39 (2014) 1266–1290.
- [50] C. Cui, H. Sadeghifar, S. Sen, D. Argyropoulos, Toward thermoplastic lignin polymers; Part II: Thermal & polymer characteristics of kraft lignin & derivatives, *Bioresources* 8 (2013) 864–886.
- [51] A. Gregorova, Z. Cibulkova, B. Kosikova, P. Simon, Stabilization effect of lignin in polypropylene and recycled polypropylene, *Polym. Degrad. Stab.* 89 (2005) 553–558.
- [52] A. S. Kabir, Z. Yuan, T. Kuboki, C. (Charles) Xu, De-polymerization of industrial lignins to improve the thermo-oxidative stability of polyolefins, *Ind. Crops Prod.* 120 (2018) 238–249.
- [53] A. S. Kabir, Effects of lignin as a stabilizer or antioxidant in polyolefins, *Electronic Thesis and Dissertation Repository The University of Western Ontario, Canada* (2017) <http://ir.lib.uwo.ca/etd/4796> (accessed September 4, 2018).
- [54] Z. Sun, B. Fridrich, A. de Santi, S. Elangovan, K. Barta, Bright side of lignin depolymerization: toward new platform chemicals, *Chem. Rev.* 118 (2018) 614–678.
- [55] W. Schutyser, T. Renders, S. Van den Bosch, S.-F. Koelewijn, G. T. Beckham, B. F. Sels, Chemicals from lignin: an interplay of lignocellulose fractionation, depolymerisation, and upgrading, *Chem. Soc. Rev.* 47 (2018) 852–908.
- [56] C. Xu, R. Arneil, D. Arancon, J. Labidi, R. Luque, Lignin depolymerisation strategies: towards valuable chemicals and fuels, *Chem. Soc. Rev.* 43 (2014) 7485–7500.
- [57] L. Dehne, C. V. Babarro, B. Saake, K. U. Schwarz, Influence of lignin source and esterification on properties of lignin-polyethylene blends, *Ind. Crops Prod.* 86 (2016) 320–328.
- [58] H. Sadeghifar, D.S. Argyropoulos, Correlations of the antioxidant properties of softwood kraft lignin fractions with the thermal stability of its blends with polyethylene, *ACS Sustain. Chem. Eng.* 3 (2015) 349–356.
- [59] P. Alexy, B. Kosikova, G. Crkonova, A. Gregorova, P. Martis, Modification of lignin-polyethylene blends with high lignin content using ethylene-vinylacetate copolymer as modifier, *J. Appl. Polym. Sci.* 94 (2004) 1855–1860.
- [60] R. R. N. Sailaja, M.V. Deepthi, Mechanical and thermal properties of compatibilized composites of polyethylene and esterified lignin, *Mater. Des.* 31 (2010) 4369–4379.
- [61] P. Alexy, B. Košíková, G. Podstránska, The effect of blending lignin with polyethylene and polypropylene on physical properties, *Polymer* 41(2000) 4901–4908.
- [62] D. Ye, J. Kong, S. Gu, Y. Zhou, C. Huang, W. Xu, X. Zhang, Selective aminolysis of acetylated lignin: Toward simultaneously improving thermal-oxidative stability and maintaining mechanical properties of polypropylene, *Int. J. Biol. Macromol.* 108 (2018) 775–781.
- [63] I. Blanco, G. Cicala, A. Latteri, G. Saccullo, A. M. M. El-Sabbagh, G. Ziegmann, Thermal characterization of a series of lignin-based polypropylene blends, *J. Therm. Anal. Calorim.* 27 (2017) 147–153.

- [64] A. V. Maldhure, J. D Ekhe, Effect of modifications of lignin on thermal, structural, and mechanical properties of polypropylene/modified lignin blends, *J. Thermoplast. Compos. Mat.* 30 (2017) 625-645.
- [65] F. Chen, H. Dai, X. Dong, J. Yang, M. Zhong, Physical properties of lignin-based polypropylene blends, *Polym. Compos.* 32 (2011) 1019-1025.
- [66] S. Kubo, J. F. Kadla. Lignin-based carbon fibers: effect of synthetic polymer blending on fiber properties. *J. Polym. Environ.* 13 (2005b) 97–105.
- [67] B. Bozsódi, V. Romhányi, P. Pataki, D. Kun, K. Renner, B. Pukánszky, Modification of interactions in polypropylene/lignosulfonate blends, *Mater. Des.* 103 (2016) 32-39.
- [68] D. Ye, S. Li, X. Lu, X. Zhang, O. J. Rojas, Antioxidant and thermal stabilization of polypropylene by addition of butylated lignin at low loadings, *ACS Sustain. Chem. Eng.* 4 (2016) 5248-5257.
- [69] A. V. Maldhure, A. R. Chaudhari, J. D. Ekhe, Thermal and structural studies of polypropylene blended with esterified industrial waste lignin, *J. Therm. Anal. Calorim.* 103 (2011) 625-632.
- [70] G. Cazacu, M. Mihaies, M. C. Pascu, L. Profire, A. L. Kowarskik, C. Vasile, Polyolefin/lignosulfonate blends, 9 functionalized polyolefin/lignin blends, *Macromol. Mater. Eng.* 289 (2004) 880-889.
- [71] B. Benjelloun-Mlayah, M. Delmas, Use of a lignin for the mechanical reinforcement of elastomers, and elastomer thus strengthened, WO2014012924A (2014).
- [72] B. Košíková, A. Gregorová, Sulfur-free lignin as reinforcing component of styrene–butadiene rubber, *J. Appl. Polym. Sci.* 97 (2005) 924-929.
- [73] X. Liu, J. Wang, J. Yu, M. Zhang, C. Wang, Y. Xu, F. Chu, Preparation and characterization of lignin based macromonomer and its copolymers with butyl methacrylate, *Int. J. Biol. Macromol.* 60 (2013) 309-315.
- [74] M. F. Silva, E. A. G. Pineda, A. A. W. Hechenleitner, D. M. Fernandes, M. K. Lima, P. R. S. Bittencourt, Characterization of poly(vinyl acetate)/sugar cane bagasse lignin blends and their photochemical degradation, *J. Therm. Anal. Calorim.* 106 (2011) 407-413.
- [75] D. Feldman, Lignin and its polyblends - A review, in: T. Q. Hu (Ed.), *Chemical modification, properties, and usage of lignin*. Kluwer Academic/Plenum Publishers, New York, 2002, pp. 81-99.
- [76] D. Feldman, D. Banu, Contribution to the study of rigid PVC polyblends with different lignins, *J. Appl. Polym. Sci.* 66 (1997) 1731-1744.
- [77] D. Feldman, D. Banu, J. Lora and S. EI-Raghi, Rigid poly(vinyl chloride) - organosolv lignin blends for applications in building, *J. Appl. Polym. Sci.* 61 (1996) 2119-2128.
- [78] D. Feldman, D. Banu, S. EI-Raghi, Poly(vinyl chloride) - lignin blends for outdoor application in building, *J. Macromol. Sci. Pure Appl. Chem. A* 31 (1994) 555-571.
- [79] D. M. Fernandes, A. A. W. Hechenleitner, A. E. Job, E. Radovanovic, E. A. G. Pineda, Thermal and photochemical stability of poly(vinyl alcohol)/modified lignin blends, *Polym. Degrad. Stab.* 91 (2006) 1192–1201.
- [80] S. Kubo, J. F. Kadla, The formation of strong intermolecular interactions in immiscible blends of poly(vinyl alcohol) (PVA) and lignin, *Biomacromolecules* 4 (2003) 561–567.
- [81] E. Zong, X. Liu, L. Liu, J. Wang, P. Song, Z. Ma, J. Ding, S. Fu, Graft polymerization of acrylic monomers onto lignin with $\text{CaCl}_2\text{-H}_2\text{O}_2$ as initiator: Preparation, mechanism, characterization, and application in poly(lactic acid), *ACS Sustain. Chem. Eng.* 6 (2018) 337-348.
- [82] O. Gordobil, R. Delucis, I. Egüés, J. Labidi, Kraft lignin as filler in PLA to improve ductility and thermal properties, *Ind. Crops Prod.* 72 (2015) 46-53.

- [83] R. Liu, L. Dai, L.-Q. Hu, W.-Q. Zhou, C.-L. Si, Fabrication of high-performance poly(L-lactic acid)/lignin-graft-poly(D-lactic acid) stereocomplex films, *Mater. Sci. Eng. C* 80 (2017) 397-403.
- [84] O. Gordobil, I. Egüés, R. Llano-Ponte, J. Labidi, Physicochemical properties of PLA lignin blends, *Polym. Degrad. Stab.* 108 (2014) 330-338.
- [85] M. Thunga, K. Chen, D. Grewell, M. R. Kessler, Bio-renewable precursor fibers from lignin/poly lactide blends for conversion to carbon fibers, *Carbon* 68 (2014) 159-166.
- [86] R. A. Pérez-Camargo, G. Saenz, S. Laurichesse, M. T. Casas, J. Puiggali, L. Avérous, A. J. Müller, Nucleation, crystallization, and thermal fractionation of poly(ϵ -caprolactone)-grafted-lignin: Effects of grafted chains length and lignin content, *J. Polym. Sci. Part B: Polym. Phys.* 53 (2015) 1736–1750.
- [87] R. Pucciariello, M. D'Auria, V. Villani, G. Shulga, Lignin/poly(ϵ -caprolactone) blends with tuneable mechanical properties prepared by high energy ball-milling, *J. Polym. Environ.* 18 (2010) 326-334.
- [88] R. Pucciariello, C. Bonin, M. D'Auria, V. Villani, G. Giammarino, G. Gorrasi, Polymer blends of steam-explosion lignin and poly(ϵ -caprolactone) by high-energy ball milling, *J. Appl. Polym. Sci.* 109 (2008) 309-313.
- [89] J. Li, Y. He, Y. Inoue, Study on thermal and mechanical properties of biodegradable blends of poly(ϵ -caprolactone) and lignin, *Polym. J.* 33 (2001) 336-343.
- [90] P. Mousavioun, P. J. Halley, W. O. S. Doherty, Thermophysical properties and rheology of PHB/lignin blends, *Ind. Crops Prod.* 50 (2013) 270–275.
- [91] P. Mousavioun, G. A. George, W. O. S. Doherty, Environmental degradation of lignin/poly(hydroxybutyrate) blends, *Polym. Degrad. Stab.* 97 (2012) 1114-1122.
- [92] P. Mousavioun, W. O. S. Doherty, G. George, Thermal stability and miscibility of poly(hydroxybutyrate) and soda lignin blends, *Ind. Crops Prod.* 32 (2010) 656-661.
- [93] K. Weihua, Y. He, N. Asakawa, Y. Inoue, Effect of lignin particles as a nucleating agent on crystallization of poly(3-hydroxybutyrate), *J. Appl. Polym. Sci.* 94 (2004) 2466-2474.
- [94] N. Lin, D. Fan, P. R. Chang, J. Yu, X. Cheng, J. Huang, Structure and properties of poly(butylene succinate) filled with lignin: A case of lignosulfonate, *J. Appl. Polym. Sci.* 121 (2011) 1717-1724.
- [95] D. Fan, P. R. Chang, N. Lin, J. H. Yu, J. Huang, Structure and properties of alkaline lignin-filled poly(butylene succinate) plastics, *Iran. Polym. J.* 20 (2011) 3-14.
- [96] S. Kubo, J. F. Kadla, Kraft lignin/poly(ethylene oxide) blends: effect of lignin structure on miscibility and hydrogen bonding, *J. Appl. Polym. Sci.* 98 (2005c) 1437–1444.
- [97] S. Kubo, J. F. Kadla, Poly(ethylene oxide)/organosolv lignin blends: Relationship between thermal properties, chemical structure, and blend behavior, *Macromolecules* 37 (2004) 6904–6911.
- [98] M. Culebras, A. Beaucamp, Y. Wang, M. M. Clauss, E. Frank, M. N. Collins, Biobased structurally compatible polymer blends based on lignin and thermoplastic elastomer polyurethane as carbon fiber precursors, *ACS Sustain. Chem. Eng.* 6 (2018) 8816–8825.
- [99] D. Feldman, M. A. Lacasse, Polymer-filler interaction in polyurethane kraft lignin polyblends, *J. Appl. Polym. Sci.* 51 (1994) 701-709.
- [100] Y. Teramoto, S.-H. Lee, T. Endo, Molecular composite of lignin: Miscibility and complex formation of organosolv lignin and its acetates with synthetic polymers containing vinyl pyrrolidone and/or vinyl acetate units, *J. Appl. Polym. Sci.* 125 (2012) 2063-2070.
- [101] M. F. Silva, C. A. da Silva, F. C. Fogo, E. A. G. Pineda, A. A. W. Hechenleitner, Thermal and FTIR study of polyvinylpyrrolidone/lignin blends, *J. Therm. Anal. Calorim.* 79 (2005) 367–370.
- [102] M. Özgür Seydibeyoğlu, A novel partially biobased PAN-lignin blend as a potential carbon fiber precursor, *J. Biomed. Biotechnol.* (2012). 598324.

- [103] N. Sallem-Idrissi, M. Sclavons, D. P Debecker, J. Devaux, Miscible raw lignin/nylon 6 blends: Thermal and mechanical performances, *J. Appl. Polym. Sci.* 133 (2016) 42963.
- [104] H. Nitz, H. Semke, R. Mulhaupt, Influence of lignin type on the mechanical properties of lignin based compounds, *Macromol Mater. Eng.* 286 (2001) 737-743.
- [105] P. C. Rodrigues, M. P. Cantao, P. Janissek, P. C.N. Scarpa, A. L. Mathias, L. P. Ramos, M.A.B. Gomes, Polyaniline/lignin blends: FTIR, MEV and electrochemical characterization, *Eur. Polym. J.* 38 (2002) 2213-2217.
- [106] G. Szabó, V. Rományi, D. Kun, K. Renner, B. Pukánszky, Competitive interactions in aromatic polymer/lignosulfonate blends, *ACS Sustain. Chem. Eng.* 5 (2017) 410-419.
- [107] M. R. Barzegari, A. Alemdar, Y. Zhang, D. Rodrigue, Mechanical and rheological behavior of highly filled polystyrene with lignin, *Polym. Compos.* 33 (2012) 353-361.
- [108] C. Liu, C. Xiao, H. Liang, Properties and structure of PVP–lignin “blend films”, *J. Appl. Polym. Sci.* 95 (2005) 1405-1411.
- [109] G. Sivasankarapillai, A. G. McDonald, Synthesis and properties of lignin-highly branched poly(ester-amine) polymeric systems, *Biomass Bioenerg.* 35 (2011) 919-931.
- [110] Q. Xing, D. Ruch, P. Dubois, L. Wu, W.-J. Wang, Biodegradable and high-performance poly(butylene adipate – co - terephthalate)–lignin UV-blocking films, *ACS Sustain. Chem. Eng.* 5 (2017) 10342-10351.
- [111] S. Luo, J. Cao, A. G. McDonald, Interfacial improvements in a green biopolymer alloy of poly(3-hydroxybutyrate-co-3-hydroxyvalerate) and lignin via in situ reactive extrusion, *ACS Sustain. Chem. Eng.* 4 (2016) 3465-3476.
- [112] F. A. Camargo, L. H. Innocentini-Mei, A. P. Lemes, S. G. Moraes, N. Duran, Processing and characterization of composites of poly(3-hydroxybutyrate-co-hydroxyvalerate) and lignin from sugar cane bagasse, *J. Compos. Mater.* 46 (2012) 417-425.
- [113] Y. Sakunkittiyut, T. Kunanopparat, P. Menut, S. Siri wattanayotin, Effect of kraft lignin on protein aggregation, functional, and rheological properties of fish protein-based material, *J. Appl. Polym. Sci.* 127 (2013) 1703-1710.
- [114] T. Kunanopparat, P. Menut, M. H. Morel, S. Guilbert, Improving wheat gluten materials properties by kraft lignin addition, *J. Appl. Polym. Sci.* 125 (2012) 1391-1399.
- [115] M. Wei, L. Fan, J. Huang, Y. Chen, Role of star-like hydroxylpropyl lignin in soy protein plastics, *Macromol. Mater. Eng.* 291 (2006) 524-530.
- [116] K. Kaewtatip, J. Thongmee, Effect of kraft lignin and esterified lignin on the properties of thermoplastic starch, *Mater. Des.* 49 (2013) 701-704.
- [117] C.-A. Teacă, R. Bodîrlău, Multi-component polymer composite/nanocomposite systems using polymer matrices from sustainable renewable sources, in: V. K. Thakur, M. K. Thakur (Eds.), *Eco-friendly polymer nano-composites: Processing and properties*, Springer, India, 2015, pp. 469-494.
- [118] C.-A. Teacă, R. Bodîrlău, D. Roşu, L. Roşu, C.-D. Varganici, Multicomponent bio-based polymer systems comprising starch and wood polymers - structure and thermal behavior, *J. Biobased Mater Bioenergy* 8 (2014) 253-260.
- [119] R. Bodîrlău, C.-A. Teacă, I. Spiridon, Influence of natural fillers on the properties of starch-based biocomposite films, *Compos. Part B* 44 (2013) 575–583.
- [120] S. Lepifre, M. Froment, F. Cazaux, S. Houot, D. Lourdin, X. Coqueret, C. Lapiere, S. Baumberger, Lignin incorporation combined with electron-beam irradiation improves the surface water resistance of starch films, *Biomacromolecules* 5 (2004) 1678–1686.
- [121] M. Pishnamazi, S. Casilagan, C. Clancy, S. Shirazian, J. Iqbal, D. Egan, C. Edlin, D. M. Croker, G. M. Walker, M. N. Collins, Microcrystalline cellulose, lactose and lignin blends: Process mapping of dry granulation via roll compaction, *Powder Technol.* Available online 3 July 2018 (<https://doi.org/10.1016/j.powtec.2018.07.003>).

- [122] S. Vincent, R. Prado, O. Kuzmina, K. Potter, J. Bhardwaj, N. D. Wanasekara, R. L. Harniman, A. Koutsomitopoulou, S. J. Eichhorn, T. Welton, S. S. Rahatekar, Regenerated cellulose and willow lignin blends as potential renewable precursors for carbon fibers, *ACS Sustain. Chem. Eng.* 6 (2018) 5903–5910.
- [123] Y. Ma, S. Asaadi, L.-S. Johansson, P. Ahvenainen, M. Reza, M. Alekhina, L. Rautkari, A. Michud, L. Hauru, M. Hummel, H. Sixta, High-strength composite fibers from cellulose–lignin blends regenerated from ionic liquid solution, *ChemSusChem* 8 (2015) 4030–4039.
- [124] A. B. Albadarin, M. N. Collins, M. Naushad, S. Shirazian, G. Walker, C. Mangwandi, Activated lignin–chitosan extruded blends for efficient adsorption of methylene blue, *Chem. Eng. J.* 307 (2017) 264–272.
- [125] M. Schreiber, S. Vivekanandhan, P. Cooke, A. K. Mohanty, M. Misra, Electrospun green fibres from lignin and chitosan: a novel polycomplexation process for the production of lignin-based fibres, *J. Mater. Sci.* 49 (2014) 7949–7958.
- [126] K. R. Aadil, A. Barapatre, H. Jha, Synthesis and characterization of *Acacia* lignin-gelatin film for its possible application in food packaging, *Bioresour. Bioprocess.* 3 (2016) 27.
- [127] R. Núñez-Flores, B. Giménez, F. Fernández-Martín, M.E. López-Caballero, M.P. Montero, M.C. Gómez-Guillén, Physical and functional characterization of active fish gelatin films incorporated with lignin, *Food Hydrocoll.* 30 (2013) 163–172.
- [128] R. Núñez-Flores, B. Giménez, F. Fernández-Martín, M.E. López-Caballero, M.P. Montero, M.C. Gómez-Guillén, Role of lignosulphonate in properties of fish gelatin films, *Food Hydrocoll.* 27 (2012) 60–71.
- [129] S. Livi, V. Bugatti, M. Marechal, B. G. Soares, G. M. O. Barra, J. Duchet-Rumeau, J.-F. Gérard, Ionic liquids–lignin combination: an innovative way to improve mechanical behaviour and water vapour permeability of eco-designed biodegradable polymer blends, *RSC Adv.* 5 (2015) 1989–1998.
- [130] B. Podolyák, D. Kun, K. Renner, B. Pukánszky, Hydrogen bonding interactions in poly(ethylene-co-vinyl alcohol)/lignin blends, *Int. J. Biol. Macromol.* 107 (2018) 1203–1211.
- [131] G. Szabó, V. Rományi, D. Kun, K. Renner, B. Pukánszky, Competitive interactions in aromatic polymer/lignosulfonate blends, *ACS Sustain. Chem. Eng.* 5 (2017) 410–419.
- [132] M. Wang, M. Leitch, C. Xu, Synthesis of phenol–formaldehyde resol resins using organosolv pine lignins, *Eur. Polym. J.* 45 (2009) 3380–3388.
- [133] N. Tachon, B. Benjelloun-Mlayah, M. Delmas, Organosolv wheat straw lignin as a phenol substitute for green phenolic resins, *BioResources* 11 (2016) 5797–5815.
- [134] A. Lee, Y. Deng, Green polyurethane from lignin and soybean oil through nonisocyanate reactions, *Eur. Polym. J.* 63 (2015) 67–73.
- [135] J. Bernardini, P. Cinelli, I. Anguillesi, M-B. Coltelli, A. Lazzeri, Flexible polyurethane foams green production employing lignin or oxypropylated lignin, *Eur. Polym. J.*, 64 (2015) 147–156.
- [136] Z. Jia, C. Lu, P. Zhou, L. Wang, Preparation and characterization of high boiling solvent lignin-based polyurethane film with lignin as the only hydroxyl group provider, *RSC Adv.* 5 (2015) 53949–53955.
- [137] C. Mu, L. Xue, J. Zhu, M. Jiang, Z. Zhou, Mechanical and thermal properties of toughened poly(L-lactic) acid and lignin blends, *BioResources* 9 (2014) 5557–5566.
- [138] M. Zhou, W. Wang, D. Yang, X. Qiu, Preparation of a new lignin-based anionic/cationic surfactant and its solution behavior, *RSC Adv.* 5 (2015) 2441–2448.
- [139] C. Gupta, N. R. Washburn, Polymer-grafted lignin surfactants prepared via reversible addition–fragmentation chain-transfer polymerization, *Langmuir* 30 (2014) 9303–9312.
- [140] B.W. Zhou, C.Y. Ha, L.L. Deng, J. Q. Mo, C. N. Sun, M. M. Shen, Preparation of surfactant with the aid of ultrasonic treatment via alkylation of sodium lignosulfonate, *Acta Polym. Sin.* 11 (2013) 1363–1368.

- [141] H. Homma, S. Kubo, T. Yamada, Y. Matsushita, Y. Uraki, Preparation and characterization of amphiphilic lignin derivatives as surfactants, *J. Wood Chem. Technol.* 28 (2008) 270-282.
- [142] Y. Qian, X. Zhong, Y. Li, X. Qiu, Fabrication of uniform lignin colloidal spheres for developing natural broad-spectrum sunscreens with high sun protection factor, *Ind. Crops Prod.* 101 (2017) 54-60.
- [143] Y. Qian, X. Qiu, S. Zhu, Sunscreen performance of lignin from different technical resources and their general synergistic effect with synthetic sunscreens, *ACS Sustain. Chem. Eng.* 4 (2016) 4029-4035.
- [144] S.R. Yearla, K. Padmasree, Preparation and characterisation of lignin nanoparticles: Evaluation of their potential as antioxidants and UV protectants, *J. Exp. Nanosci.* 11 (2016) 289-302.
- [145] Y. Qian, X. Qiu, S. Zhu, Lignin: A nature-inspired sun blocker for broad-spectrum sunscreens, *Green Chem.* 17 (2015) 320-324.
- [146] D. Barana, S. D. Ali, A. Salanti, M. Orlandi, L. Castellani, T. Hanel, L. Zoia, Influence of lignin features on thermal stability and mechanical properties of natural rubber compounds, *ACS Sustain. Chem. Eng.* 4 (2016) 5258-5267.
- [147] L. Liu M. Qian, P. Song, G. Huang, Y. Yu, S. Fu, Fabrication of green lignin-based flame retardants for enhancing the thermal and fire retardancy properties of polypropylene/wood composites, *ACS Sustain. Chem. Eng.* 4 (2016) 2422-2431.
- [148] L. Liu, G. Huang, P. Song, Y. Yu, S. Fu, Converting industrial alkali lignin to biobased functional additives for improving fire behavior and smoke suppression of polybutylene succinate, *ACS Sustain. Chem. Eng.* 4 (2016) 4732-4742.
- [149] G. P. Mendis, M. Dietenberger, S. G. Weiss, J. P. Youngblood, J. A. Howarter, M. Korey, C. R. Boardman, Phosphorylated lignin as a halogen-free flame retardant additive for epoxy composites, *Green Mater.* (2016) 1-10.
- [150] L. Ferry, G. Dorez, A. Taguet, B. Otazaghine, J.M. Lopez-Cuesta, Chemical modification of lignin by phosphorus molecules to improve the fire behavior of polybutylene succinate, *Polym. Degrad. Stab.* 113 (2015) 135-143.
- [151] J. Zhang, E. Fleury, Y. Chen, M.A. Brook, Flame retardant lignin-based silicone composites, *RSC Adv.* 5 (2015) 103907-103914.
- [152] Y. Yu, S. Fu, P. Song, Y. Jiewan, et al., Functionalized lignin by grafting phosphorus-nitrogen improves the thermal stability and flame retardancy of polypropylene, *Polym. Degrad. Stab.* 97 (2012) 541-546.
- [153] A. Guilhen, R. Gadioli, F. C. Fernandes, W. R. Waldman, M. Aurelio De Paoli, High-density green polyethylene biocomposite reinforced with cellulose fibers and using lignin as antioxidant, *J. Appl. Polym. Sci.* 134 (2017) 45219.
- [154] D. Spasojević, D. Zmejkoski, J. Glamočlija, M. Nikolić, M. Soković, V. Milošević, I. Jarić, M. Stojanović, E. Marinković, T. Barisani-Asenbauer, R. Prodanović, M. Jovanović, K. Radotić, Lignin model compound in alginate hydrogel: a strong antimicrobial agent with high potential in wound treatment, *Int. J. Antimicrob. Agents* 48 (2016) 732-735.
- [155] S. Erakovic, A. Jankovic, G. C. P. Tsui, C.-Y. Tang, V. Miskovic-Stankovic, T. Stevanovic, Novel bioactive antimicrobial lignin containing coatings on titanium obtained by electrophoretic deposition, *Int. J. Mol. Sci.*, 15 (2014) 12294-12322.
- [156] Z. Peng, Y. Zou, S. Xu, W. Zhong, W. Yang, High-performance biomass-based flexible solid-state supercapacitor constructed of pressure-sensitive lignin-based and cellulose hydrogels, *ACS Appl. Mater. Interfaces* 10 (2018) 22190-22200.
- [157] H. C. Ho, N. A. Nguyen, K. M. Meek, D. M. Alonso, S. H. Hakim, A. K. Naskar, A solvent-free synthesis of lignin-derived renewable carbon with tunable porosity for supercapacitor electrodes, *ChemSusChem.* 11 (2018) 2953-2959.

- [158] S. Hu, Y.-L. Hsieh, Lignin derived activated carbon particulates as an electric supercapacitor: carbonization and activation on porous structures and microstructures, *RSC Adv.* 7 (2017) 30459-30468.
- [159] S. Hu, S. Zhang, N. Pan, Y.-L. Hsieh, High energy density supercapacitors from lignin derived submicron activated carbon fibers in aqueous electrolytes, *J. Power Sources* 270 (2014) 106-112.
- [160] W. Farhat, R. Venditti, N. Mignard, M. Taha, F. Becquart, A. Ayoub, Polysaccharides and lignin based hydrogels with potential pharmaceutical use as a drug delivery system produced by a reactive extrusion process, *Int. J. Biol. Macromol.* 104 (2017) 564-575.
- [161] H. Mainka, O. Täger, E. Körner, L. Hilfert, S. Busse, F. T. Edelman, A. S. Herrmann, Lignin – an alternative precursor for sustainable and cost-effective automotive carbon fiber, *J. Mater. Res. Technol.* 4 (2015) 283-296.
- [162] M. Norgren, H. Edlund, Lignin: Recent advances and emerging applications, *Curr. Opin. Colloid Interface Sci.* 19 (2014) 409-416.
- [163] Y. Li, S. Sarkanen, Thermoplastics with very high lignin contents, in: W. G. Glasser, R. A. Northey, T. P. Schultz (Eds.), *Lignin: Historical, Biological, and Materials Perspectives*, ACS Symposium Series, vol. 742, American Chemical Society, Washington, DC, 1999, pp. 351-366.
- [164] J. S. Lupoi, S. Singh, R. Parthasarathi, B.A. Simmons, R.J. Henry, Recent innovations in analytical methods for the qualitative and quantitative assessment of lignin, *Renew. Sust. Energ. Rev.* 49 (2015) 871-906.
- [165] D. Kun, B. Pukánszky, Polymer/lignin blends: Interactions, properties, applications, *Eur. Polym. J.* 93 (2017) 618-641.
- [166] X. Wang, J. Zhao, Encapsulation of the herbicide picloram by using polyelectrolyte biopolymers as layer-by-layer materials, *J. Agric. Food. Chem.* 61 (2013) 3789-3796.
- [167] D. Stewart, Lignin as a base material for materials applications: Chemistry, application and economics, *Ind. Crops Prod.* 27 (2008) 202-207.
- [168] Y.L. Chung, J.V. Olsson, R.J. Li, C.W. Frank, R.M. Waymouth, S.L. Billington, *et al.*, A renewable lignin–lactide copolymer and application in biobased composites, *ACS Sustain. Chem. Eng.* 1 (2013) 1231-1238.
- [169] W.J. Mulder, R.J.A. Gosselink, M.H. Vingerhoeds, P.F.H. Harmsen, D. Eastham, Lignin based controlled release coatings, *Ind. Crop. Prod.* 34 (2011) 915-920.
- [170] X.Y. Du, L.B. Li, M.E. Lindström, Modification of industrial softwood kraft lignin using Mannich reaction with and without phenolation pretreatment, *Ind. Crops Prod.* 52 (2014) 729-735.
- [171] H. F. Zhou, H. M. Lou, D. J. Yang, J. Y. Zhu, X. Q. Qiu, Lignosulfonate to enhance enzymatic saccharification of lignocelluloses: role of molecular weight and substrate lignin, *Ind. Eng. Chem. Res.* 52 (2013) 8464-8470.
- [172] H. M. Lou, J. Y. Zhu, T. Q. Lan, H. R. Lai, X. Q. Qiu, pH-induced lignin surface modification to reduce nonspecific cellulase binding and enhance enzymatic saccharification of lignocelluloses, *ChemSusChem* 6 (2013) 919-927.
- [173] Z. J. Wang, T. Q. Lan, J. Y. Zhu, Lignosulfonate and elevated pH can enhance enzymatic saccharification of lignocelluloses, *Biotechnol. Biofuels* 6 (2013) 1-10.
- [174] H. M. Lou, H. F. Zhou, X. L. Li, M. X. Wang, J. Y. Zhu, X. Q. Qiu, Understanding the effects of lignosulfonate on enzymatic saccharification of pure cellulose, *Cellulose* 21 (2014) 1352-1359.
- [175] C. Crestini, M. Crucianelli, M. Orlandi, R. Saladino, Oxidative strategies in lignin chemistry: a new environmental friendly approach for the functionalisation of lignin and lignocellulosic fibers, *Catal. Today* 156 (2010) 8-22.

- [176] D. H. Nagaraju, T. Rebis, R. Gabrielsson, A. Elfwing, G. Milczarek, O. Inganäs, Charge storage capacity of renewable biopolymer/conjugated polymer interpenetrating networks enhanced by electroactive dopants, *Adv. Energy Mater.* 4 (2014) 1-7.
- [177] O. Caballero-Calero, P. Diaz-Chao, B. Abad, C.V. Manzano, M.D. Ynsa, J.J. Romero, *et al.*, Improvement of bismuth telluride electrodeposited films by the addition of sodium lignosulfonate, *Electrochim. Acta* 123 (2014) 117-126.
- [178] B. L. Xue, J. L. Wen, R. C. Sun, Lignin-based rigid polyurethane foam reinforced with pulp fiber: Synthesis and characterization, *ACS Sustain. Chem. Eng.* 1 (2014) 1474-1480.
- [179] L. Klapiszewski, M. Nowacka, G. Milczarek, T. Jesionowski, Physicochemical and electrokinetic properties of silica/lignin biocomposites, *Carbohydr. Polym.* 94 (2013) 345-355.
- [180] D. Kai, M. J. Tan, P. L. Chee, Y. K. Chua, Y. L. Yap, X. J. Loh, Towards lignin-based functional materials in a sustainable world, *Green Chem.* 18 (2016) 1175-1200.
- [181] S. Lu, S. Li, J. Yu, D. Guo, R. Ling, B. Huang, The effect of hyperbranched polymer lubricant as a compatibilizer on the structure and properties of lignin/polypropylene composites, *Wood Mater. Sci. Eng.* 8(3) (2013) 159-165.
- [182] R. Liu, Y. Peng, J. Cao, Y. Chen, Comparison on properties of lignocellulosic flour/polymer composites by using wood, cellulose, and lignin flours as fillers, *Compos. Sci. Technol.* 103 (2014) 1-7.
- [183] K. Liu, S.A. Madbouly, J.A. Schrader, M.R. Kessler, D. Grewell, W.R. Graves, Biorenewable polymer composites from tall oil-based polyamide and lignin-cellulose fiber, *J. Appl. Polym. Sci.* 132 (2015) 42592.
- [184] H. Naegele, J. Pfitzer, L. Ziegler, E.R. Inone-Kauffmann, N. Eisenreich, Applications of lignin materials and their composites, in: O. Faruk, M. Sain (Eds.), *Lignin in polymer composites*, Elsevier Inc., Amsterdam, 2016, pp. 233-244.
- [185] B. Del Saz-Orozco, M. Oliet, M.V. Alonso, E. Rojo, F. Rodriguez, Formulation optimization of unreinforced and lignin nanoparticle-reinforced phenolic foams using an analysis of variance approach, *Compos. Sci. Technol.* 72 (2012) 667-674.
- [186] M. Tortora, F. Cavalieri, P. Mosesso, F. Ciaffardini, F. Melone, C. Crestini, Ultrasound driven assembly of lignin into microcapsules for storage and delivery of hydrophobic molecules, *Biomacromolecules* 15 (2014) 1634-1643.
- [187] C. Jiang, H. He, H. Jiang, L. Ma, D.M. Jia, Nano-lignin filled natural rubber composites: preparation and characterization, *eXPRESS Polym. Lett.* 7 (2013) 480-493.
- [188] P. Figueiredo, K. Lintinen, A. Kiriazis, V. Hynninen, Z. Liu, T. Bauleth-Ramos, A. Rahikkala, A. Correia, T. Kohout, B. Sarmento, J. Yli-Kauhaluoma, J. Hirvonen, O. Ikkala, M.A. Kostianen, H.A. Santos, *In vitro* evaluation of biodegradable lignin-based nanoparticles for drug delivery and enhanced antiproliferation effect in cancer cells, *Biomaterials* 121 (2017) 97-108.
- [189] F. K. Ko, A. Goudarzi, L.T. Lin, Y. Li, J. F. Kadla, Lignin-based composite carbon nanofibers, in: O. Faruk, M. Sain (Eds.), *Lignin in polymer composites*, Elsevier Inc., Amsterdam, 2016, pp. 167-194.
- [190] E. Fortunati, W. Yang, F. Luzi, J. Kenny, L. Torre, D. Puglia, Lignocellulosic nanostructures as reinforcement in extruded and solvent casted polymeric nanocomposites: an overview, *Eur. Polym. J.* 80 (2016) 295-316.
- [191] W. Yang, E. Fortunati, F. Dominici, G. Giovanale, A. Mazzaglia, G.M. Balestra, J.M. Kenny, D. Puglia, Synergic effect of cellulose and lignin nanostructures in PLA based systems for food antibacterial packaging, *Eur. Polym. J.* 79 (2016) 1-12.
- [192] H. Nagele, J. Pfitzer, E. Nagele, E.R. Inone, N. Eisenreich, W. Eckl, P. Eyerer, Arboform - A thermoplastic, processable material from lignin and natural fibers, in: T.Q. Hu

- (Ed.), Chemical Modification, Properties, and Usage of Lignin, Kluwer Academic/Plenum Publishers, New York, USA, 2002, pp. 101-120.
- [193] N. Okuda, M. Sato, Manufacture and mechanical properties of binderless boards from kenaf core, *J. Wood Sci.* 50(1) (2004) 53-61.
- [194] M. Tajuddin, Z. Ahmad, H. Ismail, A review of natural fibers and processing operations for the production of binderless boards, *BioResources* 11 (2016) 5600-5617.
- [195] S. Sahoo, M. Misra, A.K. Mohanty, Enhanced properties of lignin-based biodegradable polymer composites using injection moulding process, *Compos. Part A* 42 (2011) 1710-1718.
- [196] S. Sahoo, M. Misra, A.K. Mohanty, Effect of compatibilizer and fillers on the properties of injection molded lignin-based hybrid green composites, *J. Appl. Polym. Sci.* 127 (2013) 4110-4121.
- [197] R. Tupciauskas, J. Gravitis, J. Abolins, A. Veveris, M. Andzs, T. Liitia, T. Tamminen, Utilization of lignin powder for manufacturing self-binding HDF, *Holzforschung*, 71 (2017) 555-556.
- [198] N. El Mansouri, A. Pizzi, J. Salvadó, Lignin-based wood panel adhesives without formaldehyde, *Eur. J. Wood Wood Prod.* 65 (2007) 65-70.
- [199] X. Zhou, F. Zheng, C. Lv, L. Tang, K. Wei, X. Liu, G. Du, Q. Yong, G. Xue, Properties of formaldehyde-free environmentally friendly lignocellulosic composites made from poplar fibres and oxygen-plasma-treated enzymatic hydrolysis lignin, *Compos. Part B* 53 (2013) 369-375.
- [200] V. Hemmilä, J. Trischler, D. Sandberg, Lignin – an adhesive raw material of the future or waste of research energy?, in: C. Brischke, L. Meyer, (Eds.), *Proc. 9th Meeting of the Northern European Network for Wood Science and Engineering (WSE)*, Hannover, Germany, September 11-12, 2013, pp. 98-103.
- [201] K. Liu, S.A. Madbouly, J.A. Schrader, M.R. Kessler, D. Grewell, W.R. Graves, Biorenewable polymer composites from tall oil-based polyamide and lignin-cellulose fiber, *J. Appl. Polym. Sci.* 132 (2015) 42592.
- [202] E. Inone-Kauffmann, N. Eisenreich, W. Eckl, E. Walschburger, H. Nagele, J. Pfitzer, Loudspeaker boxes from lignin matrix composites, PPS23 in: *Proceedings of the Polymer Processing Society, Annual Meeting, San Salvador, Brazil, 2007.*
- [203] T. Haensel, A. Comouth, N. Zydziak, *et al.*, Pyrolysis of wood-based polymer compounds, *J. Anal. Appl. Pyrol.* 87 (2010) 124-128.
- [204] J. Jordan, K.I. Jacob, R. Tannenbaum, *et al.*, Experimental trends in polymer nanocomposites – a review, *Mater. Sci. Eng. A* 393 (2005) 1-11.
- [205] G. Droval, J. F. Feller, P. Salagnac, P. Glouannec, Conductive polymer composites with double percolated architecture of carbon nanoparticles and ceramic microparticles for high heat dissipation and sharp PTC switching, *Smart Mater. Struct.* 17(2) (2008) 1-10.
- [206] G. Devi, V.J. Rao, Room temperature synthesis of colloidal platinum nanoparticles, *Bull. Mater. Sci.* 23 (2000) 467-470.
- [207] H. Nagele, J. Pfitzer, L. Ziegler, E. R. Inone-Kauffmann, W. Eckl, N. Eisenreich, Lignin matrix composites from natural resources – ARBOFORM[®], in: S. Kabasci (Ed.), *Bio-based plastics: Materials and applications*, First Edition, John Wiley & Sons, Ltd., Chichester, UK, 2014, pp. 89-115.
- [208] N. Guigo, L. Vincent, A. Mija, H. Naegele, N. Sbirrazzuoli, Innovative green nanocomposites based on silicate clays/lignin/natural fibres, *Compos. Sci. Technol.* 69 (2009) 1979-1984.
- [209] X. Xu, Z. He, S. Lu, D. Guo, J. Yu, Enhanced thermal and mechanical properties of lignin/polypropylene wood-plastic composite by using flexible segment-containing reactive compatibilizer, *Macromol. Res.* 22 (2014) 1084-1089.

- [210] S. Lu, S. Li, J. Yu, D. Guo, R. Ling, B. Huang, The effect of hyperbranched polymer lubricant as a compatibilizer on the structure and properties of lignin/polypropylene composites, *Wood Mater. Sci. Eng.* 8 (2013) 159-165.
- [211] Y. Peng, R. Liu, J. Cao, Characterization of surface chemistry and crystallization behavior of polypropylene composites reinforced with wood flour, cellulose, and lignin during accelerated weathering, *Appl. Surf. Sci.* 332 (2015) 253-259.
- [212] G. Toriz, F. Denes, R.A. Young, Lignin-polypropylene composites. Part 1: composites from unmodified lignin and polypropylene, *Polym. Compos.* 23 (2002) 806-813.
- [213] B. Kosikova, A. Revajova, V. Demianova, The effect of adding lignin on modification of surface properties of polypropylene, *Eur. Polym. J.* 31 (1995) 953-956.
- [214] G. Toriz, J. Ramos, R.A. Young, Lignin-polypropylene composites. II. Plasma modification of kraft lignin and particulate polypropylene, *J. App. Polym. Sci.* 91 (2004) 1920-1926.
- [215] L. Hu, T. Stevanovic, D. Rodrigue, Unmodified and esterified kraft lignin-filled polyethylene composites: compatibilization by free-radical grafting, *J. Appl. Polym. Sci.* 132 (2015) 41484.
- [216] X. Lv, Z. Gao, Y. Zhang, M. Di, Mechanical study and microscopic characterization of lignin/PE composites, *Adv. Mater. Res. (Trans Tech Publications)* 335 (2011a) 191-194.
- [217] X. Lv, Y. Zhang, M. Di, Effect of PP-G-MAH on the compatibility of lignin/LDPE composites, *Adv. Mater. Res. (Trans Tech Publications)* 194 (2011b) 1476-1479.
- [218] X. Lv, Q. Liu, Y. Zhang, M. Di, Compatibility of lignin/LDPE composites modified with HDPE-g-MAH, *Adv. Mater. Res. (Trans Tech Publications)* 181-182 (2011c) 88-91.
- [219] X. Lv, Y. Zhang, M. Di, Z. Gao, Effect of different compatibilizing agents on the compatibility of lignin/LDPE composites, *Adv. Mater. Res. (Trans Tech Publications)* 391 (2012) 143-146.
- [220] A. Diop, F. Mijiyawa, D. Koffi, B.V. Kokta, D. Montplaisir, Study of lignin dispersion in low-density polyethylene, *J. Thermoplast. Compos. Mater.* 28 (2015) 1662-1674.
- [221] S. Casenve, A. Ait-Wi, B. Riedl, Mechanical behaviour of highly filled lignin/polyethylene composites made by catalytic grafting, *Can. J. Chem. Eng.* 74 (1996) 308-315.
- [222] N. N. Jabber, The study of bacterial growth on low-density-polyethylene-lignin composite, *Basra J. Vet. Res.* 10 (2011) 97-105.
- [223] S.K. Samal, E.G. Fernandes, A. Corti, E. Chiellini, Bio-based polyethylene-lignin composites containing a pro-oxidant/pro-degradant additive: preparation and characterization, *J. Polym. Environ.* 22 (2014) 58-68.
- [224] J. Zhou, X. Luo, Preparation of lignin/LDPE-EVA composition and foam, *J. Chem. Ind. Eng. (China)* 58 (2007) 1834.
- [225] M.R. Barzegari, A. Alemdar, Y. Zhang, D. Rodrigue, Thermal analysis of highly filled composites of polystyrene with lignin. *Polym. Polym. Compos.* 21(6) (2013) 357-366.
- [226] W.K. El-Zawawy, M.M. Ibrahim, M.N. Belgacem, A. Dufresne, Characterization of the effects of lignin and lignin complex particles as fillers on a polystyrene film, *Mater. Chem. Phys.* 131 (2011) 348-357.
- [227] S.L. Hilburg, A.N. Elder, H. Chung, R.L. Ferebee, M.R. Bockstaller, N.R. Washburn, A universal route towards thermoplastic lignin composites with improved mechanical properties, *Polymer* 55 (2014) 995-1003.
- [228] P.R.S. Bittencourt, D.M. Fernandes, M.F. Silva, M.K. Lima, A.A.W. Hechenleitner, E.A.G. Pineda, Lignin modified by formic acid on the PA6 films: evaluation on the morphology and degradation by UV radiation, *Waste Biomass Valorization* 1 (2010) 323-328.
- [229] F. Liu, K. Xu, M. Chen, D. Cao, The rheological and mechanical properties of PVC-lignin blends, *Int. Polym. Process.* 27 (2012) 121-127.

- [230] F. Liu, K. Xu, M. Chen, D. Cao, Thermal stability of PVC-lignin blends miscibilized by poly(ethyl acrylate-co-acrylic acid), *CIESC Journal* 63(10) (2012) 3324-3329.
- [231] Y. Yu, P. Song, C. Jin, S. Fu, L. Zhao, Q. Wu, J. Ye, Catalytic effects of nickel (cobalt or zinc) acetates on thermal and flammability properties of polypropylene-modified lignin composites, *Ind. Eng. Chem. Res.* 51 (2012) 12367-12374.
- [232] F. Liu, K. Xu, M. Chen, D. Cao, The roles of polyacrylate in poly(vinyl chloride)-lignin composites, *Polym. Compos.* 32 (2011) 1399-1407.
- [233] Ł. Klapiszewski, J. Tomaszewska, K. Skórczewska, T. Jesionowski, Preparation and characterization of eco-friendly Mg(OH)₂/lignin hybrid material and its use as a functional filler for poly(vinyl chloride), *Polymers* 9 (2017) 258-277.
- [234] Ł. Klapiszewski, F. Pawlak, J. Tomaszewska, T. Jesionowski, Preparation and characterization of novel PVC/silica–lignin composites, *Polymers* 7 (2015) 1767-1788.
- [235] S. S. Nair, S. Sharma, Y. Pu, Q. Sun, S. Pan, J. Y. Zhu, Y. Deng, A. J. Ragauskas, High shear homogenization of lignin to nanolignin and thermal stability of nano-lignin-polyvinyl alcohol blends, *ChemSusChem*. 7 (2014) 3513-3520.
- [236] Y. Li, X. Lin, X. Zhuo, X. Luo, Poly(vinyl alcohol)/quaternized lignin composite adsorbent: synthesis, characterization and application for nitrate adsorption, *J. Appl. Polym. Sci.* 128 (2013) 2746-2752.
- [237] L. Su, G. Fang, Characterization of crosslinked alkaline lignin/poly(vinyl alcohol) film with a formaldehyde cross-linker, *BioResources* 9 (2014) 4477-4488.
- [238] P. Song, Z. Cao, S. Fu, Z. Fang, Q. Wu, J. Ye, Thermal degradation and flameretardancy properties of ABS/lignin: effects of lignin content and reactive compatibilization, *Thermochim. Acta* 518 (2011) 59-65.
- [239] J. Jeong, J. Park, S. Kim, J. Lee, N. Ahn, H. Roh, Preparation and characterization of thermoplastic polyurethanes using partially acetylated kraft lignin, *Fiber Polym.* 14 (2013) 1082-1093.
- [240] G. Stiubianu, A. Nistor, A. Vlad, M. Cazacu, Modification of water sorption capacity of polydimethylsiloxane based composites by incorporation of lignin, *Mater. Plast.* 48 (2011) 289-294.
- [241] G. Stiubianu, M. Cazacu, M. Cristea, A. Vlad, Polysiloxane-lignin composites, *J. Appl. Polym. Sci.* 13 (2009) 2313-2321.
- [242] Z. W. He, L. H. He, J. Yang, Q. F. Lu, Removal and recovery of Au(III) from aqueous solution using low-cost lignin-based biosorbent, *Ind. Eng. Chem. Res.* 52 (2013) 4103-4108.
- [243] M. Nowacka, L. Klapiszewski, M. Norman, T. Jesionowski, Dispersive evaluation and surface chemistry of advanced multifunctional silica/lignin hybrid biomaterials, *Cent. Eur. J. Chem.* 11 (2013) 1860-1873.
- [244] L. Klapiszewski, M. Madrawska, T. Jesionowski, Preparation and characterisation of hydrated silica/lignin biocomposites, *Physicochem. Probl. Miner. Process.* 48 (2012) 463-473.
- [245] Y. Dessie, S. Admassie, Electrochemical study of conducting polymer/lignin composites, *Orient. J. Chem.* 29 (2013) 1359-1369.
- [246] M. Canetti, F. Bertini, Influence of the lignin on thermal degradation and melting behavior of poly(ethylene terephthalate) based composites, *e-Polymers* 9 (2009) 596-605.
- [247] G. Engelmann, J. Ganster, Lignin reinforcement in thermosets composites, in: O. Faruk, M. Sain (Eds.), *Lignin in polymer composites*, Elsevier Inc., Amsterdam, 2016, pp. 119-151.
- [248] L.I. Grishechko, G. Amaral-Labat, A. Szczurek, V. Fierro, A. Kuznetsov, A. Celzard, Lignin-phenol-formaldehyde aerogels and cryogels, *Micropor. Mesopor. Mat.* 168 (2013) 19-29.
- [249] J. Batog, A. Przepiera, Enzymatic processing of lignin in the production of lignocellulosic composites, *Cell. Chem. Technol.* 45 (2011) 503-505.

- [250] S. Sarkar, B. Adhikari, Synthesis and characterization of lignin-HTPB copolyurethane, *Eur. Polym. J.* 37 (2001) 1391-1401.
- [251] S. Sarkar, B. Adhikari, Thermal stability of lignin - hydroxy-terminated polybutadiene copolyurethanes, *Polym. Degrad. Stab.* 73 (2001) 169-175.
- [252] X. Luo, A. Mohanty, M. Misra, Lignin as a reactive reinforcing filler for water-blown rigid biofoam composites from soy oil-based polyurethane, *Ind. Crops Prod.* 47 (2013) 13-19.
- [253] H. Jeong, J. Park, S. Kim, J. Lee, N. Ahn, Compressive viscoelastic properties of softwood kraft lignin-based flexible polyurethane foams, *Fiber Polym.* 14 (2013) 1301-1310.
- [254] M. Lacasse, D. Feldman, Swelling and adhesion characteristics of lignin-filled polyurethane sealant, *J. Adhes. Sci. Technol.* 8 (1994) 473-484.
- [255] S. Sahoo, M. Misra, A. K. Mohanty, Enhanced properties of lignin-based biodegradable polymer composites using injection moulding process, *Compos. Part A* 42 (2011) 1710-1718.
- [256] S. Sahoo, M. Misra, A. K. Mohanty, Effect of compatibilizer and fillers on the properties of injection molded lignin-based hybrid green composites, *J. Appl. Polym. Sci.* 127 (2013) 4110-4121.
- [257] F. Bertini, M. Canetti, A. Cacciamani, G. Elegir, M. Orlandi, L. Zoia, Effect of lignoderivatives on thermal properties and degradation behavior of poly(3-hydroxybutyrate)-based biocomposites, *Polym. Degrad. Stab.* 97 (2012) 1979-1987.
- [258] M. Canetti, M. Urso, P. Sadocco, Influence of the morphology and of the supermolecular structure on the enzymatic degradation of bacterial poly(3-hydroxybutyrate), *Polymer* 40 (1999) 2587-2594.
- [259] E.S. Stevens, A. Klamczynski, G.M. Glenn, Starch-lignin foams, *eXPRESS Polym. Lett.* 4 (2010) 311-320.
- [260] R. Wu, X. Wang, F. Li, H.-Z. Li, Y. Wang, Green composite films prepared from cellulose, starch and lignin in room temperature ionic liquid, *Bioresour. Technol.* 100 (2009) 2569-2574.
- [261] I. Spiridon, C.-A. Teacă, R. Bodirlău, Preparation and characterization of adipic acid-modified starch microparticles/plasticized starch composite films reinforced by lignin, *J. Mater. Sci.* 46 (2011) 3241-3251.
- [262] F. Le Digabel, L. Averous, Effects of lignin content on the properties of lignocellulose-based biocomposites, *Carbohydr. Polym.* 66 (2006) 537-545.
- [263] M.A. Rahman, D. De Santis, G. Spagnoli, G. Ramorino, M. Penco, V. T. Phuong, A. Lazzeri, Biocomposites based on lignin and plasticized poly (L-lactic acid), *J. Appl. Polym. Sci.* 129 (2013) 202-214.
- [264] J. Zhu, L. Xue, C. Mu, M. Jiang, Z. Zhou, Modification of lignin with silane coupling agent to improve the interface of poly(L-lactic) acid/lignin composites, *BioResources* 10(3) (2015) 4315-4325.
- [265] Y. Sun, L. Yang, X. Lu, C. He, Biodegradable and renewable poly(lactide)-lignin composites: synthesis, interface and toughening mechanism, *J. Mater. Chem. A* 3 (2015) 3699-3709.
- [266] R. Liu, Y. Peng, J. Cao, Y. Chen, Comparison on properties of lignocellulosic flour/polymer composites by using wood, cellulose, and lignin flours as fillers, *Compos. Sci. Technol.* 103 (2014) 1-7.
- [267] S. H. Botros, M. A. M. Eid, Z. A. Nageeb, Thermal stability and dielectric relaxation of natural rubber/soda lignin and natural rubber/thiolignin composites, *J. Appl. Polym. Sci.* 99 (2006) 2504-2511.
- [268] J. Sajeev, M.I. Jeoju, A. Roselin, Mechanical properties of natural rubber composites reinforced with lignin from *Caryota* fibre, *Int. J. Emerging Technol. Adv. Eng.* 4 (2014) 567-570.

- [269] P. Frigerio, L. Zoia, M. Orlandi, T. Hanel, L. Castellani, Application of sulphur-free lignins as a filler for elastomers: Effect of hexamethylenetetramine treatment, *BioResources* 9 (2014) 1387-1400.
- [270] C. Jiang, H. He, X.J. Yao, P. Yu, L. Zhou, D.M. Jia, Solvent diffusion in silica/poly [styrene-co-(acrylic acid)] core-shell microspheres by pulsed field gradient NMR techniques, *J. Appl. Polym. Sci.* 131 (2014) 9.
- [271] A. Rangan, M.V. Manjula, K.G. Satyanarayana, R. Menon, Lignin/nanolignin and their biodegradable composites, in: S. Kalia (Ed.), *Biodegradable green composites*, John Wiley & Sons Inc., Hoboken, New Jersey, USA, 2016, pp. 167-198.
- [272] W. Zhao, B. Simmons, S. Singh, A. Ragauskas, G. Cheng, From lignin association to nano-/micro-particle preparation: extracting higher value of lignin, *Green Chem.* 18 (2016) 5693-5700.
- [273] C. Thulluri, S.R. Pinnamaneni, P.R. Shetty, U. Addepally, Synthesis of lignin-based nanomaterials/nanocomposites: Recent trends and future perspectives, *Ind. Biotechnol.* 12 (2016) 153-160.
- [274] M. Pishnamazi, S. Casilagan, C. Clancy, S. Shirazian, J. Iqbal, D. Egan, C. Edlin, D.M. Croker, G.M. Walker, M.N. Collins, Microcrystalline cellulose, lactose and lignin blends: Process mapping of dry granulation via roll compaction, *Powder Technol.* 2018; <https://doi.org/10.1016/j.powtec.2018.07.003>
- [275] S. Thakur, P.P. Govender, M.A. Mamo, S. Tamulevicius, Y.K. Mishra, V.K. Thakur, Progress in lignin hydrogels and nanocomposites for water purification: Future perspectives, *Vacuum* 146 (2017) 342-355.
- [276] P.K. Mishra, R. Wimmer, Aerosol assisted self-assembly as a route to synthesize solid and hollow spherical lignin colloids and its utilization in layer by layer deposition, *Ultrason. Sonochem.* 35 (2017) 45-50.
- [277] C. Frangville, M. Rutkevicius, A.P. Richter, O.D. Velez, S.D. Stoyanov, V.N. Paunov, Fabrication of environmentally biodegradable lignin nanoparticles, *Chem. Phys. Chem.* 13 (2012) 4235-4243.
- [278] Y. Qian, Y. Deng, X. Qiu, H. Li, D. Yang, Formation of uniform colloidal spheres from lignin, a renewable resource recovered from pulping spent liquor, *Green Chem.* 16 (2014) 2156-2163.
- [279] A. P. Richter, J. S. Brown, B. Bharti, A. Wang, S. Gangwal, K. Houck *et al.*, An environmentally benign antimicrobial nanoparticle based on a silver-infused lignin core, *Nat. Nanotechnol.* 10 (2015) 817-823.
- [280] A. K. Gupta, S. Mohanty, S. K. Nayak, Influence of addition of vapor grown carbon fibers on mechanical, thermal and biodegradation properties of lignin nanoparticle filled biopoly(trimethylene terephthalate) hybrid nanocomposites, *RSC Adv.* 5 (2015) 56028-56036.
- [281] A.A. Myint, H.W. Lee, B. Seo, W.-S. Son, J. Yoon, T.J. Yoon *et al.*, One pot synthesis of environmentally friendly lignin nanoparticles with compressed liquid carbon dioxide as an antisolvent, *Green Chem.* 18 (2016) 2129-2146.
- [282] Y. Qian, X. Qiu, X. Zhong, D. Zhang, Y. Deng, D. Yang, *et al.*, Lignin reverse micelles for uvabsorbing and high mechanical performance thermoplastics, *Ind. Eng. Chem. Res.* 54 (2015) 12025-12030.
- [283] T. E. Nypelo, C. A. Carrillo, O. J. Rojas, Lignin supracolloids synthesized from (W/O) microemulsions: use in the interfacial stabilization of Pickering systems and organic carriers for silver metal, *Soft Matter* 11 (2015) 2046-2054.
- [284] X. Liu, H. Yin, Z. Zhang, B. Diao, J. Li, Functionalization of lignin through ATRP grafting of poly(2-dimethylaminoethyl methacrylate) for gene delivery, *Colloids Surf. B* 125 (2015) 230-237.

- [285] I. A. Gilca, V. I. Popa, C. Crestini, Obtaining lignin nanoparticles by sonication, *Ultrason. Sonochem.* 23 (2015) 369-375.
- [286] M. Lievonen, J.J. Valle-Delgado, M.-L. Mattinen, E.-L. Hult, K. Lintinen, M.A. Kostiainen *et al.*, A simple process for lignin nanoparticle preparation, *Green Chem.* 18 (2016) 1416-1422.
- [287] K. Lintinen, M. Latikka, M.H. Sipponen, R.H.A. Ras, M. Osterberg, M.A. Kostiainen, Structural diversity in metal-organic nanoparticles based on iron isopropoxide treated lignin, *RSC Adv.* 6 (2016) 31790-31796.
- [288] M. Ago, S. Huan, M. Borghei, J. Raula, E.I. Kauppinen, O.J. Rojas, High-throughput synthesis of lignin particles (approximately 30 nm to approximately 2 μ m) *via* aerosol flow reactor: size fractionation and utilization in Pickering emulsions, *ACS Appl. Mater. Interfaces* 8 (2016) 23302-23310.
- [289] K. S. Gilmore, C. Gupta, N. R. Washburn, Tunable Pickering emulsions with polymer-grafted lignin nanoparticles (PGLNs), *J. Colloid Interf. Sci.* 466 (2016) 91-100.
- [290] A. Rangan, M.V. Manchiganti, R.M. Thilavidankan, S. G. Kestur, R. Menon, Novel method for the preparation of lignin-rich nanoparticles from lignocellulosic fibers, *Ind. Crops Prod.* 103 (2017) 152-160.
- [291] X. Fuquan, Y. Han, S. Wang, G. Li, T. Qin, Y. Chen, F. Chu, Preparation and formation mechanism of size-controlled lignin nanospheres by self-assembly, *Ind. Crops Prod.* 100 (2017) 146-152.
- [292] W. Yang, J. S. Owczarek, E. Fortunati, M. Kozanecki, A. Mazzaglia, G. M. Balestra, J. M. Kenny, L. Torre, D. Puglia, Antioxidant and antibacterial lignin nanoparticles in polyvinyl alcohol/chitosan films for active packaging, *Ind. Crops Prod.* 94 (2016) 800-811.
- [293] W. Yang, F. Dominici, E. Fortunati, J. M. Kenny, D. Puglia, Effect of lignin nanoparticles and masterbatch procedures on the final properties of glycidyl methacrylate-g-poly (lactic acid) films before and after accelerated UV weathering, *Ind. Crops Prod.* 77 (2015) 833-844.
- [294] D. Kai, W. Ren, L. Tian, P.L. Chee, Y. Liu, S. Ramakrishna *et al.*, Engineering poly(lactide)-lignin nanofibers with antioxidant activity for biomedical application, *ACS Sustain. Chem. Eng.* 4 (2016) 5268-5276.
- [295] D. Kai, K. Zhang, L. Jiang, H.Z. Wong, Z. Li, Z. Zhang, *et al.*, Sustainable and antioxidant lignin-polyester copolymers and nanofibers for potential healthcare applications, *ACS Sustain. Chem. Eng.* 5 (2017) 6016-6025.
- [296] D. Kai, S. Jiang, Z.W. Low, X.J. Loh, Engineering highly stretchable lignin-based electrospun nanofibers for potential biomedical applications, *J. Mater. Chem. B* 3 (2015) 6194-6204.
- [297] C. Salas, M. Ago, L.A. Lucia, O.J. Rojas, Synthesis of soy protein-lignin nanofibers by solution electrospinning, *React. Funct. Polym.* 85 (2014) 221-227.
- [298] M. Ago, J.E. Jakes, L.S. Johansson, S. Park, O.J. Rojas, Interfacial properties of lignin based electrospun nanofibers and films reinforced with cellulose nanocrystals, *ACS Appl. Mater. Interf.* 4 (2012) 6849-6856.
- [299] M. Ago, J.E. Jakes, O.J. Rojas, Thermomechanical properties of lignin-based electrospun nanofibers and films reinforced with cellulose nanocrystals: A dynamic mechanical and nanoindentation study, *ACS Appl. Mater. Interf.* 5 (2013) 11768-11776.
- [300] D. Yiamsawas, G. Baier, E. Thines, K. Landfester, F.R. Wurm, Biodegradable lignin nanocontainers, *RSC Adv.* 4 (2014) 11661-11663.
- [301] H. Li, Y. Deng, B. Liu, Y. ren, j. liang, y. qian, *et al.*, preparation of nanocapsules via the Self-Assembly of Kraft Lignin: A totally green process with renewable resources, *ACS Sustain. Chem. Eng.* 4 (2016) 1946-1953.

- [302] N. Chen, L.A. Dempere, Z. Tong, Synthesis of pH-Responsive lignin-based nanocapsules for controlled release of hydrophobic molecules, *ACS Sustain. Chem. Eng.* 4 (2016) 5204-5211.
- [303] E. Ten, C. Ling, Y. Wang, A. Srivastava, L.A. Dempere, W. Vermerris, Lignin nanotubes as vehicles for gene delivery into human cells, *Biomacromolecules* 15 (2014) 327-338.
- [304] P. Goulis, I.A. Kartsonakis, K. Mpalias, C. Charitidis, Combined effects of multi-walled carbon nanotubes and lignin on polymer fiber-reinforced epoxy composites, *Mater. Chem. Phys.* 218 (2018) 18-27.
- [305] M. Grzegorz, Kraft lignin as dispersing agent for carbon nanotubes, *J. Electroanal. Chem.* 638(1) (2010) 178-181.
- [306] W. Yang, E. Fortunati, F. Dominici, G. Giovanale, A. Mazzaglia, G. M. Balestra, J. M. Kenny, D. Puglia, Effect of cellulose and lignin on disintegration, antimicrobial and antioxidant properties of PLA active films, *Int. J. Biol. Macromol.* 89 (2016) 360-368.
- [307] W. Yang, E. Fortunati, F. Dominici, G. Giovanale, A. Mazzaglia, G. M. Balestra, J. M. Kenny, D. Puglia, Synergic effect of cellulose and lignin nanostructures in PLA based systems for food antibacterial packaging, *Eur. Polym. J.* 79 (2016) 1-12.
- [308] W. Yang, M. Rallini, D-Y. Wang, D. Gao, F. Dominici, L. Torre, J. M. Kenny, D. Puglia, Role of lignin nanoparticles in UV resistance, thermal and mechanical performance of PMMA nanocomposites prepared by a combined free-radical graft polymerization/masterbatch procedure, *Compos. Part A* 107 (2017) 61-69.
- [309] W. Liu, R. Zhou, D. Zhou, G. Ding, J. M. Soah, C. Y. Yue, X. Lu, Lignin-assisted direct exfoliation of graphite to graphene in aqueous media and its application in polymer composites, *Carbon* 83 (2015) 188-197.
- [310] K. Chaochanchaikul, K. Jayaraman, V. Rosarpitak, N. Sombatsompop, Influence of lignin content on photodegradation in wood/HDPE composites under UV weathering, *BioResources* 7 (2012) 38-55.
- [311] E.M. Fernandes, I.M. Aroso, J.F. Mano, J.A. Covas, R.L. Reis, Functionalized cork-polymer composites (CPC) by reactive extrusion using suberin and lignin from cork as coupling agents, *Compos. Part B* 67 (2014) 371-380.
- [312] L. Hu, T. Stevanovic, D. Rodrigue, Comparative study of polyethylene composites containing industrial lignins, *Polym. Polym. Compos.* 23 (2015) 369-374.
- [313] S. Lu, S. Li, J. Yu, D. Guo, R. Ling, B. Huang, The effect of hyperbranched polymer lubricant as a compatibilizer on the structure and properties of lignin/polypropylene composites, *Wood Mater. Sci. Eng.* 8 (2013) 159-165.
- [314] X. Xu, Z. He, S. Lu, D. Guo, J. Yu, Enhanced thermal and mechanical properties of lignin/polypropylene wood-plastic composite by using flexible segment-containing reactive compatibilizer, *Macromol. Res.* 22 (2014) 1084-1089.
- [315] R. Gadioli, J. A. Morais, W. R. Waldman, M.-A. De Paoli, The role of lignin in polypropylene composites with semi-bleached cellulose fibers: mechanical properties and its activity as antioxidant, *Polym. Degrad. Stab.* 108 (2014) 23-34.
- [316] R. Liu, Y. Peng, J. Cao, Y. Chen, Comparison on properties of lignocellulosic flour/polymer composites by using wood, cellulose, and lignin flours as fillers, *Compos. Sci. Technol.* 103 (2014) 1-7.
- [317] J.-S. Yeo, D.-W. Seong, S.-H. Hwang, Chemical surface modification of lignin particle and its application as filler in the polypropylene composites, *J. Ind. Eng. Chem.* 31 (2015) 80-85.
- [318] M. Canetti, F. Bertini, Supermolecular structure and thermal properties of poly(ethylene terephthalate)/lignin composites, *Compos. Sci. Technol.* 67 (2007) 3151-3157.

- [319] H. Jeong, J. Park, S. Kim, J. Lee, N. Ahn, H. Roh, Preparation and characterization of thermoplastic polyurethanes using partially acetylated kraft lignin, *Fiber Polym.* 14 (2013) 1082-1093.
- [320] C. Zhang, H. Wu, M. R. Kessler, High bio-content polyurethane composites with urethane modified lignin as filler, *Polymer* 69 (2015) 52-57.
- [321] M. N. Garcia Gonzalez, M. Levi, S. Turri, G. Griffini, Lignin nanoparticles by ultrasonication and their incorporation in waterborne polymer nanocomposites *J. Appl. Polym. Sci.* 2017, 45318.
- [322] K. Akato, C. D. Tran, J. Chen, A. K. Naskar, Poly(ethylene oxide)-assisted macromolecular self-assembly of lignin in ABS matrix for sustainable composite applications, *ACS Sustain. Chem. Eng.* 3 (2015) 3070-3076.
- [323] H. P. S. A. Khalil, M. M. Marliana, T. Alshammari, Material properties of epoxy-reinforced biocomposites with lignin from empty fruit bunch as curing agent, *BioResources* 6 (2011) 5206-5223.
- [324] Y. Xie, Q.-F. Lu, Y. Jin, X. Cheng, Enzymatic hydrolysis lignin epoxy resin modified asphalt, *Adv. Mater. Res.* 239-242 (2011) 3346-3349.
- [325] Q. Yin, W. Yang, C. Sun, M. Di, Preparation and properties of lignin-epoxy resin composite, *BioResources* 7 (2012) 5737-5748.
- [326] X. Kong, Z. Xu, L. Guan, M. Di, Study on polyblending epoxy resin adhesive with lignin curing temperature. *Int. J. Adhes. Adhes.* 48 (2014) 75-79.
- [327] G. Engelmann, J. Ganster, Bio-based epoxy resins with low molecular weight kraft lignin and pyrogallol. *Holzforschung* 68 (2014) 435-446.
- [328] W. Doherty, P. Halley, L. Edye, D. Rogers, F. Cardona, Y. Park, T. Woo, Studies on polymers and composites from lignin and fiber derived from sugar cane, *Polym. Adv. Technol.* 18 (2007) 673-678.
- [329] W.-J. Lee, K.-C. Chang, I.-M. Tseng, Properties of phenol-formaldehyde resins prepared from phenol-liquefied lignin. *J. Appl. Polym. Sci.* 124 (2012) 4782-4788.
- [330] J. F. Stanzione, P. A. Giangiulio, J. M. Sadler, J. J. La Scala, R.P. Wool, Lignin-based bio-oil mimic as biobased resin for composite applications, *ACS Sustain. Chem. Eng.* 1 (2013) 419-426.
- [331] S. Xiao, J. Feng, J. Zhu, X. Wang, C. Yi, S. Su, Preparation and characterization of lignin-layered double hydroxide/styrene butadiene rubber composites, *J. Appl. Polym. Sci.* 130 (2013) 1308-1312.
- [332] P. Frigerio, L. Zoia, M. Orlandi, T. Hanel, L. Castellani, Application of sulphur-free lignins as a filler for elastomers: effects of hexamethylenetetramine treatment, *BioResources* 9 (2014) 1387-1400.
- [333] P. Yu, H. He, Y. Jia, S. Tian, J. Chen, D. Jia, Y. Luo, A comprehensive study on lignin as a green alternative of silica in natural rubber composites, *Polym. Test.* 54 (2016) 176-185.
- [334] D. Barana, S.D. Ali, A. Salanti, M. Orlandi, L. Castellani, T. Hanel, L. Zoia, Influence of lignin features on thermal stability and mechanical properties of natural rubber compounds, *ACS Sustain. Chem. Eng.* 4 (2016) 5258–5267.
- [335] Y. Ikeda, T. Phakkeeree, P. Junkong, H. Yokohama, P. Phinyocheep, R. Kitano, A. Kato, Reinforcing biofiller “Lignin” for high performance green natural rubber nanocomposites, *RSC Adv.* 7 (2017) 5222-5231.
- [336] S. Otani, Y. Fukuoka, B. Igarashi, K. Sasaki, Method for producing carbonized lignin fiber, U.S. Patent No. 3461082 Washington D.C. (1969).
- [337] I. Tomizuka, T. Kurita, Y. Tanaka, O. Watanabe, Voids in the carbon fibers produced from lignin and PVA, *Nippon Seram Kyo Gak.* 79 (1971) 460-469.
- [338] D. J. Johnson, I. Tomizuka, O. Watanabe, The fine structure of lignin-based carbon fibres, *Carbon* 13 (1975) 321-325.

- [339] K. Sudo, K. Shimizu, N. Nakashima, A. Yokoyama, A new modification method of exploded lignin for the preparation of a carbon fiber precursor, *J. Appl. Polym. Sci.* 48 (1993) 1485-1491.
- [340] Uraki, Y., Kubo, S., Nigo, N., Sano, Y., & Sasaya, T. (1995). Preparation of carbon fibers from organosolv lignin obtained by aqueous acetic acid pulping. *Holzforschung* 49(4), 343-350.
- [341] J. F. Kadla, S. Kubo, R. A. Venditti, R. D. Gilbert, A. L. Compere, W. Griffith, Lignin-based carbon fibers for composite fiber applications, *Carbon* 40 (2002) 2913-2920.
- [342] S. Kubo, J. F. Kadla, Lignin-based carbon fibers: Effect of synthetic polymer blending on fiber properties, *J. Polym. Environ.* 13 (2005) 97-105.
- [343] S. P. Maradur, C. H. Kim, S. Y. Kim, B.-H. Kim, W. C. Kim, K. S. Yang, Preparation of carbon fibers from a lignin copolymer with polyacrylonitrile, *Synth. Met.* 162 (2012) 453-459.
- [344] J. Lin, S. Kubo, T. Yamada, K. Koda, Y. Uraki, Chemical thermostabilization for the preparation of carbon fibers from softwood lignin, *BioResources* 7 (2012) 5634-5646.
- [345] J. Lin, K. Koda, S. Kubo, T. Yamada, M. Enoki, Y. Uraki, Improvement of mechanical properties of softwood lignin-based carbon fibers, *J. Wood Chem. Technol.* 34 (2014). 111-121.
- [346] H. C. Liu, A. T. Chien, B. A. Newcomb, Y. Liu, S. Kumar, Processing, structure, and properties of lignin- and CNT-incorporated polyacrylonitrile-based carbon fibers, *ACS Sustain. Chem. Eng.* 3 (2015) 1943-1954.
- [347] S. Wang, Y. Li, H. Xiang, Z. Zhou, T. Chang, M. Zhu, Low cost carbon fibers from bio-renewable lignin/poly (lactic acid) (PLA) blends, *Compos. Sci. Technol.* 119 (2015) 20-25.
- [348] W. Qu, Y. Xue, Y. Gao, M. Rover, X. Bai, Repolymerization of pyrolytic lignin for producing carbon fiber with improved properties, *Biomass Bioenergy* 95 (2016) 8-26.
- [349] J. Jin, J. Ding, A. S. Klett, M. C. Thies, A. A. Ogale, Carbon fibers derived from fractionated-solvated lignin precursors for enhanced mechanical performance, *ACS Sustain. Chem. Eng.* (2018) DOI: 10.1021/acssuschemeng.8b02697
- [350] G. Vazquez, J. Gonzalez, S. Freire, G. Antorrena, Effect of chemical modification of lignin on the glue bond performance of lignin-phenolic resins, *Bioresour. Technol.* 60 (1997) 191-198.
- [351] A. R. Mahendran, G.E. Wuzella, N. Aust, U. Mueller, A. Kandelbauer, Processing and characterization of natural fibre reinforced composites using lignin phenolic binder, *Polym. Polym. Compos.* 21 (2013) 199-205.
- [352] A. Tejado, C. Pena, J. Labidi, J.M. Echeverria, I. Mondragon, Physico-chemical characterization of lignins from different sources for use in phenol-formaldehyde resin synthesis, *Bioresour. Technol.* 98 (2007) 1655-1663.
- [353] T. Akhtar, G. Lutfullah, Z. Ullah, Lignosulfonate-phenol formaldehyde adhesive: A potential binder for wood panel industries, *J. Chem. Soc. Pak.* 33 (2011) 535-538.
- [354] J. C. Dominguez, M. Oliet, M. V. Alonso, E. Rojo, F. Rodriguez, Structural, thermal and rheological behavior of a bio-based phenolic resin in relation to a commercial resol resin, *Ind. Crops Prod.* 42 (2013) 308-314.
- [355] Y. Matsushita, S. Wada, K. Fukushima, S. Yasuda, Surface characteristics of phenol-formaldehyde-lignin resin determined by contact angle measurement and inverse gas chromatography, *Ind. Crops Prod.* 23 (2006) 115-121.
- [356] A. Donmez Cavdar, H. Kalaycioglu, S. Hiziroglu, Some of the properties of oriented strandboard manufactured using kraft lignin phenolic resin, *J. Mater. Process. Technol.* 202 (2008) 559-563.

- [357] L. Kouisni, Y. Fang, M. Paleologou, B. Ahvazi, J. Hawari, Y. Zhang, Kraft lignin recovery and its use in the preparation of lignin-based phenol formaldehyde resins for plywood, *Cell. Chem. Technol.* 45 (2011) 515-520.
- [358] A. D. Cavdar, H. Kalaycioglu, S. Hiziroglu, Some of the properties of oriented strandboard manufactured using kraft lignin phenolic resin, *J. Mater. Process. Technol.* 202 (2008) 559-563.
- [359] Y. Park, W. Doherty, P.J. Halley, Developing lignin-based resin coatings and composites, *Ind. Crops Prod.* 27 (2008) 163-167.
- [360] W. Qiao, S. Li, G. Guo, S. Han, S. Ren, Y. Ma, Synthesis and characterization of phenol-formaldehyde resin using enzymatic hydrolysis lignin, *J. Ind. Eng. Chem.* 21 (2015) 1417-1422.
- [361] S. J. Lee, H. J. Kim, E. J. Cho, Y. Song, H.-J. Bae, Isolation and characterization of lignin from the oak wood bioethanol production residue for adhesives, *Int. J. Biol. Macromol.* 72 (2015) 1056-1062.
- [362] M. Wang, M. Leitch, C. Xu, Synthesis of phenol-formaldehyde resin resins using organosolv pine lignins, *Eur. Polym. J.* 45 (2009) 3380-3388.
- [363] W. Zhang, Y. Ma, Y. Xu, C. Wang, F. Chu, Lignocellulosic ethanol residue-based lignin-phenol-formaldehyde resin adhesive, *Int. J. Adhes. Adhes.* 40 (2013) 11-18.
- [364] Z. Jing, H. Lihong, L. Bingchuan, B. Caiying, J. Puyou, Z. Yonghong, Preparation and characterization of novolac phenol-formaldehyde resins with enzymatic hydrolysis lignin, *J. Taiwan Inst. Chem. Eng.* 54 (2015) 178-182.
- [365] Y.B. Mu, C.P. Wang, L.W. Zhao, F.X. Chu, Study on composite adhesive of hydroxymethylated liginosulfonate/phenol-formaldehyde resin with low free formaldehyde, *Chem. Ind. Forest. Prod.* 29 (2009) 38-42.
- [366] S. Cheng, Z. Yuan, M. Anderson, M. Leitch, C. Xu, Synthesis of biobased phenolic resins/adhesives with methylolated wood-derived bio-oil, *J. Appl. Polym. Sci.* 126 (2012) E431-E441.
- [367] A. Moubarik, N. Grimi, N. Boussetta, A. Pizzi, Isolation and characterization of lignin from Moroccan sugar cane bagasse: Production of lignin-phenol-formaldehyde wood adhesive, *Ind. Crops Prod.* 45 (2013) 296-302.
- [368] W. Zhang, Y. Ma, C. Wang, S. Li, M. Zhang, F. Chu, Preparation and properties of lignin-phenol-formaldehyde resins based on different biorefinery residues of agricultural biomass, *Ind. Crops Prod.* 43 (2013) 326-333.
- [369] C. Mancera, N.-E. El Mansouri, F. Vilaseca, F. Ferrando, J. Salvado, The effect of lignin as a natural adhesive on the physico-mechanical properties of *vitis vinifera* fiberboards, *BioResources* 6 (2011) 2851-2860.
- [370] Y. Jin, X. Cheng, Z. Zheng, Preparation and characterization of phenol-formaldehyde adhesives modified with enzymatic hydrolysis lignin, *Bioresour. Technol.* 101 (2010) 2046-2048.
- [371] A. Pizzi, Recent developments in eco-efficient bio-based adhesives for wood bonding: opportunities and issues, *J. Adhesion. Sci. Technol.* 20 (2006) 829-846.
- [372] N.-E. El Mansouri, A. Pizzi, J. Salvado, Lignin-based polycondensation resins for wood adhesives. *J. Appl. Polym. Sci.* 103 (2007) 1690-1699.
- [373] H. R. Mansouri, P. Navarrete, A. Pizzi, S. Tapin-Lingua, B. Benjelloun-Mlayah, H. Pasch, S. Rigolet, Synthetic-resin-free wood panel adhesives from mixed low molecular mass lignin and tannin, *Eur. J. Wood Wood Prod.* 69 (2011) 221-229.
- [374] N.-E. El Mansouri, Q. Yuan, F. Huang, Study of chemical modification of alkaline lignin by the glyoxalation reaction, *BioResources* 6 (2011) 4523-4536.
- [375] N.-E. El Mansouri, A. Pizzi, J. Salvado, Lignin-based wood panel adhesives without formaldehyde, *Holz Roh Werkst.* 65 (2007) 65-70.

- [376] E. C. Ramires, J. D. Megiatto Jr, C. Gardrat, A. Castellan, E. Frollini, Biobased composites from glyoxal-phenolic resins and sisal fibers, *Bioresour. Technol.* 101 (2010) 1998-2006.
- [377] P. Dongre, M. Driscoll, T. Amidon, B. Bujanovic, Lignin-furfural based adhesives, *Energies* 8 (2015) 7897-7914.
- [378] C. G. da Silva, S. Grelier, F. Pichavant, E. Frollini, A. Castellan, Adding value to lignins isolated from sugarcane bagasse and *Miscanthus*, *Ind. Crops Prod.* 42 (2013) 87-95.
- [379] H. Lei, A. Pizzi, G. Du, Environmentally friendly mixed tannin/lignin wood resins, *J. Appl. Polym. Sci.* 107 (2008) 203-209.
- [380] G. Foyer, B.H. Chanfi, B. Boutevin, S. Caillol, G. David, New method for the synthesis of formaldehyde-free phenolic resins from lignin-based aldehyde precursors, *Eur. Polym. J.* 74 (2016) 296-309.
- [381] X. Geng, K. Li, Investigation of wood adhesives from kraft lignin and polyethylenimine, *J. Adhes. Sci. Technol.* 20 (2006) 847-858.
- [382] Y. Liu, K. Li, Preparation and characterization of demethylated lignin-polyethylenimine adhesives, *J. Adhes.* 82 (2006) 593-605.
- [383] Y. Yuan, M.H. Guo, F. Y. Liu, Preparation and evaluation of green composites using modified ammonium lignosulfonate and polyethylenimine as a binder, *BioResources* 9 (2014) 836-848.
- [384] N. Guigo, A. Mija, L. Vincent, N. Sbirrazzuoli, Eco-friendly composite resins based on renewable biomass resources: Polyfurfuryl alcohol/lignin thermosets. *Eur. Polym. J.* 46 (2010) 1016-1023.
- [385] X. Zhou, F. Zheng, C. Lv, L. Tang, K. Wei, X. Liu, G. Du, Q. Yong, G. Xue, Properties of formaldehyde-free environmentally friendly lignocellulosic composites made from poplar fibres and oxygen-plasma-treated enzymatic hydrolysis lignin, *Compos. Part B Eng.* 53 (2013) 369-375.
- [386] S. Kalami, M. Arefmanesh, E. Master, M. Nejad, Replacing 100% of phenol in phenolic adhesive formulations with lignin, *J. Appl. Polym. Sci.* 134 (2017) 45124.
- [387] H. Ito, N. Shiraishi, Epoxy Resin Adhesives from Thiolignin, *Mokuzai Gakkaishi*, 33 (1987) 393-399.
- [388] N. Shiraishi, Recent progress in wood dissolution and adhesives from Kraft lignin, in: *ACS Symposium Series*, 397 (1989) 488-495.
- [389] Q. Yin, W. Yang, C. Sun, M. Di, Preparation and properties of lignin-epoxy resin composite, *BioResources* 7 (2012) 5737-5748.
- [390] C. I. Simionescu, V. Rusan, G. Cazacu, M. M. Macoveanu, R. Lipsa, G. Stoica, Lignin-epoxy resins. III. Physical and chemical characterization of solid products, *Cell. Chem. Technol.* 24 (1990) 397-405.
- [391] C. I. Simionescu, V. Rusan, M. M. Macoveanu, G. Cazacu, R. Lipsa, A. Stoleriu, A. Ioanid, Crosslinked lignin-epoxy resins, *Cell. Chem. Technol.* 25 (1991) 355-368.
- [392] C. I. Simionescu, V. Rusan, C. I. Turta, S.A. Bobcova, M. M. Macoveanu, G. Cazacu, A. Stoleriu, Synthesis and characterization of some iron-lignosulfonate based lignin-epoxy resins, *Cell. Chem. Technol.* 27 (1993) 627-644.
- [393] L. L. Kosbar, J. D. Gelorme, R. M. Japp, W. T. Fotorny, Introducing biobased materials into the electronics industry, *J. Ind. Ecol.* 4 (2001) 93-105.
- [394] G. Cazacu, M. C. Pascu, L. Profire, A. I. Kowarski, M. Mihaes, C. Vasile, Lignin role in a complex polyolefin blend, *Ind. Crops Prod.* 20 (2004) 261-227.
- [395] H. Wang, Q. Hao, X. Yang, L. Lu, X. Wang, Graphene oxide doped polyaniline for supercapacitors, *Electrochem. Comm.* 11 (2009) 1158-1161.

- [396] K. Wang, P. Zhao, X. Zhou, H. Wu, Z. Wei, Flexible supercapacitors based on cloth-supported electrodes of conducting polymer nanowire array/SWCNT composites, *J. Mater. Chem.* 21 (2011) 16373-16378.
- [397] B. Zhang, F. Kang, J.M. Tarascon, J.K. Kim, Recent advances in electrospun carbon nanofibers and their application in electrochemical energy storage, *Progr. Mater. Sci.* 76 (2016) 319-380.
- [398] C. Lai, Z. Zhou, L. Zhang, X. Wang, Q. Zhou, Y. Zhao, Y. Wang, X.F. Wu, Z. Zhu, H. Fong, Free-standing and mechanically flexible mats consisting of electrospun carbon nanofibers made from a natural product of alkali lignin as binder-free electrodes for high-performance supercapacitors, *J. Power Sources* 247 (2014) 134-141.
- [399] X. You, K. Koda, T. Yamada, Y. Uraki, Preparation of electrode for electric double layer capacitor from electrospun lignin fibers, *Holzforschung* 69 (2015) 1097-1106.
- [400] X. You, J. Duan, K. Koda, T. Yamada, Y. Uraki, Preparation of electric double layer capacitors (EDLCs) from two types of electrospun lignin fibers, *Holzforschung* 70 (2016) 661-671.
- [401] D. Lei, X.D. Li, M.K. Seo, M.S. Khil, H.Y. Kim, B.S. Kim, NiCo₂O₄ nanostructure-decorated PAN/lignin based carbon nanofiber electrodes with excellent cyclability for flexible hybrid supercapacitors, *Polymer* 132 (2017) 31-40.
- [402] S.X. Wang, L. Yang, L.P. Stubbs, X. Li, C. He, Lignin-derived fused electrospun carbon fibrous mats as high performance anode materials for lithium ion batteries, *ACS Appl. Mater. Interfaces* 5 (2013) 12275-12282.
- [403] J. Jin, B.J. Yu, Z.Q. Shi, C.Y. Wang, C.B. Chong, Lignin-based electrospun carbon nanofibrous webs as free-standing and binder-free electrodes for sodium ion batteries, *J. Power Sources* 272 (2014) 800-807.
- [404] F. Zamboni, S. Vieira, R.L. Reis, J.M. Oliveira, M.N. Collins, The potential of hyaluronic acid in immunoprotection and immunomodulation: Chemistry, processing and function, *Progr. Mater. Sci.* 97 (2018) 97-122.
- [405] V.K. Thakur, M.K. Thakur, Recent advances in green hydrogels from lignin: a review, *Int. J. Biol. Macromol.* 72 (2015) 834-847.
- [406] W.K. El-Zawawy, Preparation of hydrogel from green polymer, *Polym. Adv. Technol.* 16 (2005) 48-54.
- [407] I.E. Raschip, C. Vasile, D. Ciolacu, G. Cazacu, Semi-interpenetrating polymer networks containing polysaccharides. Xanthan/Lignin networks, *High Perform. Polym.* 19 (2007) 603-620.
- [408] L. Passauer, K. Fischer, F. Liebner, Preparation and physical characterization of strongly swellable oligo (oxyethylene) lignin hydrogels, *Holzforschung* 65 (2011) 309-317.
- [409] Z. Peng, F. Chen, Synthesis and properties of lignin-based polyurethane hydrogels, *Int. J. Polym. Mater.* 60 (2011) 674-683.
- [410] Q. Yao, J. Xie, J. Liu, H. Kang, Y. Liu, Adsorption of lead ions using a modified lignin hydrogel, *J. Polym. Res.* 21 (2014) 465 (16 pages).
- [411] Y. Wang, Y. Xiong, J. Wang, X. Zhang, Ultrasonic-assisted fabrication of montmorillonite-lignin hybrid hydrogel: Highly efficient swelling behaviors and super-sorbent for dye removal from wastewater, *Colloid Surf. A: Physicochem. Eng. Asp.* 520 (2017) 903-913.
- [412] D. Kai, Z.W. Low, S.S. Liow, A. Abdul Karim, H. Ye, G. Jin, K. Li, X.J. Loh, Development of lignin supramolecular hydrogels with mechanically responsive and self-healing properties, *ACS Sust. Chem. Eng.* 3 (2015) 2160-2169.
- [413] X. Wang, Z. Zhou, X. Guo, Q. He, C. Hao, C. Ge, Ultrasonic-assisted synthesis of sodium lignosulfonate-grafted poly (acrylic acid-co-poly (vinyl pyrrolidone)) hydrogel for drug delivery, *RSC Advances* 6 (2016) 35550-35558.

- [414] L. Musilová, A. Mráček, A. Kovalcik, P. Smolka, A. Minařík, P. Humpolíček, R. Vícha, P. Ponížil, Hyaluronan hydrogels modified by glycinated Kraft lignin: Morphology, swelling, viscoelastic properties and biocompatibility, *Carbohydr. Polym.* 181(2018) 394-403.
- [415] H. Bian, L. Wei, C. Lin, Q. Ma, H. Dai, J.Y. Zhu, Lignin-containing cellulose nanofibril-reinforced polyvinyl alcohol hydrogels, *ACS Sustain. Chem. Eng.* 6 (2018) 4821-4828.
- [416] M. Han, A. Jayakumar, Z. Li, Q. Zhao, J. Zhang, X. Jiang, X. Guo, R. Wang, C. Xu, S. Song, J. M. Lee, Fabricating 3D macroscopic graphene-based architectures with outstanding flexibility by the novel liquid drop/colloid flocculation approach for energy storage applications, *ACS Appl. Mater. Interfaces* 10 (2018) 21991-22001.
- [417] M. Michelin, S. Liebentritt, A.A. Vicente, J.A. Teixeira, Lignin from an integrated process consisting of liquid hot water and ethanol organosolv: Physicochemical and antioxidant properties, *Int. J. Biol. Macromol.* 120 (2018) 159–169.
- [418] A. García, A. Toledano, M.Á. Andrés, J. Labidi, Study of the antioxidant capacity of *Miscanthus sinensis* lignins, *Process Biochem.* 45 (2010) 935–940.
- [419] T. Dizhbite, G. Telysheva, V. Jurkjane, U. Viesturs, Characterization of the radical scavenging activity of lignins—natural antioxidants, *Bioresour. Technol.* 95 (2004) 309–317.
- [420] F. Chen, Y. Tobimatsu, D. Havkin-Frenkel, R.A. Dixon, J. Ralph, A polymer of caffeyl alcohol in plant seeds, *Proc. Natl. Acad. Sci.* 109 (2012) 1772–1777.
- [421] F. Chen, Y. Tobimatsu, L. Jackson, J. Nakashima, J. Ralph, R.A. Dixon, Novel seed coat lignins in the Cactaceae: structure, distribution and implications for the evolution of lignin diversity, *Plant J.* 73 (2013) 201–211.
- [422] Y. Li, L. Shuai, H. Kim, A.H. Motagamwala, J.K. Mobley, F. Yue, Y. Tobimatsu, D. Havkin-Frenkel, F. Chen, R.A. Dixon, J.S. Luterbacher, J.A. Dumesic, J. Ralph, An “ideal lignin” facilitates full biomass utilization, *Sci. Adv.* (2018) 11.
- [423] L. Berstis, T. Elder, M. Crowley, G.T. Beckham, Radical Nature of C-Lignin, *ACS Sustain. Chem. Eng.* 4 (2016) 5327–5335.
- [424] E.L. Mahon, S.D. Mansfield, Tailor-made trees: engineering lignin for ease of processing and tomorrow’s bioeconomy, *Curr. Opin. Biotechnol.* 56 (2019) 147–155.
- [425] M. Nar, H.R. Rizvi, R.A. Dixon, F. Chen, A. Kovalcik, N. D’Souza, Superior plant based carbon fibers from electrospun poly-(caffeyl alcohol) lignin, *Carbon.* 103 (2016) 372–383.
- [426] N. Dalton, R. P. Lynch, M.N. Collins, M. Culebras. Thermoelectric properties of electrospun carbon nanofibres derived from lignin, *Int. J. Biol. Macromol.* 121 (2019) 472-479.
- [427] C.A. Murphy, J.B. Costa, J. Silva-Correia, J.M. Oliveira, R.L. Reis, M.N. Collins, Biopolymers and polymers in the search of alternative treatments for meniscal regeneration: State of the art and future trends, *Appl. Mater. Today* 12 (2018) 51-71.